

Rust-Oleum® Industrial Brands Sierra Performance™ Specification

Coating Specification for Rust-Oleum Virtual Solutions Coating Solution 38 A water based coating system

Epoxy Acrylic Enamel S16/S22
For Concrete Substrates in a Mild Industrial Environment

Specification Prepared by: Rust-Oleum Technical Service, July 2005

This is a general coating specification. Changes to this specification may void any product warranties. Contact your Rust-Oleum representative or Rust-Oleum Technical Service if modifications are required to better meet your needs.



PART I GENERAL

1.01 SCOPE OF WORK

- A.** Provide all materials and labor necessary to install Sierra Performance Epoxy Acrylic Enamel in strict accordance with project drawings, specifications and current Rust-Oleum Corporation application instructions.

1.02 RELATED WORK BY OTHER (SELECT AS NEEDED)

- A.** Division 3 Concrete
- B.** Division 4 Masonry
- C.** Division 5 Metals
- D.** Division 6 Wood
- E.** Division 7 Thermal & Moisture Protection
- F.** Division 10 Specialties
- G.** Division 11 Special Construction

1.03 SYSTEM DESCRIPTION

- A.** The Sierra Performance Epoxy Acrylic Enamel is a zero VOC, and zero HAPs, waterbased two component acrylic/epoxy enamel manufactured by Rust-Oleum Corporation, located at 11 Hawthorn Parkway, Vernon Hills, IL 60061 (847) 367-7700. The Sierra Performance Epoxy Acrylic Enamel is suitable for interior use on properly prepared and primed, or previously coated, surfaces in mild to moderate industrial environments.

1.04 ENGINEERING AND DESIGN REQUIREMENTS

- A.** The Design Architect and Project Engineer shall be responsible for all decisions pertaining to design, detail, and structural capability. Rust-Oleum Corporation has written specifications, technical data and application information to assist in the design and engineering processes.
- B.** Equivalent materials of other manufacturers may be substituted on approval of the engineer or designer. These requests for substitution shall include manufacturer's literature for each product giving the name, resin type, descriptive information, volume solids, and recommended dry film thickness. A list of a minimum of ten (10) projects where the coating system has been applied and performed to expectations for at least three (3) years service is also required. No requests for substitution shall be considered that lower system film thickness, number of coats and/or change the resin type of the specified coating. Equivalent product substitutions will be accepted only from the Contractor and will be considered only after the contract has been awarded.
- C.** Custom colors are available for a nominal charge per color set-up from Rust-Oleum Corporation.
- D.** The Sierra Performance Epoxy Acrylic Enamel is not suitable for water immersion applications.
- E.** The Sierra Performance Epoxy Acrylic Enamel can be used in USDA-regulated facilities based on FSIS Directive 11,000.4 (Rev. 4), November 24, 1995.

1.05 SURFACE PREPARATION AND APPLICATION DESCRIPTION

- A.** Substrate cleaning, surface preparation, coating application and dry film thickness shall be as specified and shall meet or exceed Rust-Oleum Corporation's recommendations.

- B. All application equipment shall be clean and maintained in proper working order in accordance with the equipment manufacturers' recommendations.
- C. The Sierra Performance Epoxy Acrylic Enamel shall be applied in accordance with the air and surface temperature limits and work areas shall be reasonably free of airborne dust during application and drying time.

1.06 PERFORMANCE REQUIREMENTS

- A. The Sierra Performance Epoxy Acrylic Enamel has been tested in accordance to the following test standards. Results are detailed on the Rust-Oleum Corporation Technical Data Sheet.

Volume Solids	50%
Recommended Dry Film Thickness (DFT)	2½-5 mils
Practical Coverage (assumes 15% material loss)	135-270 sq ft/gal
VOC	0 g/l (0 lbs/gal)
Mixing ratio S16 S22	3:1 4:1 Part 1: Part 2 by volume
Dry Time (@ 70F/21C and 50% RH)	
Tack Free	30 minutes
Handle	1-2 hours
Recoat	1-2 hours

1.07 QUALITY ASSURANCE

- A. Applicator Qualifications:
 1. Shall be knowledgeable in the proper installation of the Sierra Performance Epoxy Acrylic Enamel and experienced in the application of a two component water based epoxy enamel.
 2. Shall provide a minimum of one (1) year workmanship warranty for the application of the Sierra Performance Epoxy Acrylic Enamel.
 3. A list of Certified Rust-Oleum Corporation Coating Applicators is available from Rust-Oleum Corporation.
- B. Pre-, Mid-, and Post-Job Conferences shall be scheduled at discretion of the Project Engineer, Design Architect, or General Contractor.

1.08 SUBMITTALS

- A. Product Data: Sierra Performance Epoxy Acrylic Enamel, application and related equipment information.
- B. Color Cards: Supply color cards of specified materials showing range of colors.
- C. Applicator: If applicable, provide certified contractor documentation showing proof of familiarity with the Sierra Performance Epoxy Acrylic Enamel.

1.09 DELIVERY STORAGE AND HANDLING

- A. Deliver the Sierra Performance Epoxy Acrylic Enamel on-site in Rust-Oleum Corporation's labeled, original, unopened containers.
- B. All materials shall be stored inside or under cover at ambient temperature. Keep materials dry, protected from elemental damage, and protect from freezing.

1.10 PROJECT CONDITIONS

- A. Protect adjacent work from damage and overspray during application of the Sierra Performance Epoxy Acrylic Enamel.
- B. Shop coat primers should be specified to accept the application the Sierra Performance Epoxy Acrylic Enamel.

1.11 WARRANTY

- A. The technical data and suggestions of use are correct to the best of our knowledge, and offered in good faith. The statements of this specification do not constitute a warranty, expressed, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.
- B. Special written project warranties may be issued on a request basis at the discretion of the Rust-Oleum Corporation Technical and Legal Departments and would not be contained within this specification document.

2. PRODUCTS

2.01 MANUFACTURER

- A. The Sierra Performance Epoxy Acrylic Enamel shall be obtained from Rust-Oleum Corporation or through a Rust-Oleum distributor. To request nearest distribution source contact Rust-Oleum Corporation.

2.02 MATERIALS

- A. The Sierra Performance Epoxy Acrylic Enamel is available in a selection of standard colors, and tint bases for field tinting operations. Contact Rust-Oleum Corporation for availability of colors and container size.
- B. S16 Semi-gloss finish
- C. S22 Satin finish

3. EXECUTION

3.01 JOB CONFERENCES

- A. A pre-job conference shall be at the discretion of the architect, engineer or general contractor. Coating contractor, substrate installer and other trades whose work affects the application of the Sierra Performance Epoxy Acrylic Enamel shall meet at the project site to review procedures and time schedule proposed for application of the Sierra

Performance Epoxy Acrylic Enamel and related work. Additional conferences are at the discretion of the architect, engineer, general contractor and/or owner.

3.02 SURFACE PREPARATION

- A.** All cleaning and surface preparations specified are minimums.
- B.** All surfaces to be coated shall be free of cracks, pits, fins, projections, or other imperfections that would interfere with the formation of a uniform, unbroken coating film. The coating contractor is to examine the substrate to determine if it is in satisfactory condition to receive the Sierra Performance Epoxy Acrylic Enamel. Obtain coating contractor's written report listing conditions detrimental to performance of work in this specification. Do not proceed with the application of the Sierra Performance Epoxy Acrylic Enamel until unsatisfactory conditions have been corrected.
- C.** All oil, grease, and chalking shall be completely removed with biodegradable degreasers prior to mechanical cleaning begins. (Rust-Oleum 3599 Cleaner Degreaser)
- D.** All loose and deteriorating concrete must be removed.
- E.** For concrete block, all voids and openings shall be pointed. Surfaces shall be filled at the discretion of the Project Engineer and/or Design Architect using Rust-Oleum Corporation 5199 Block Filler.
- F.** Concrete surfaces being coated must be protected against moisture transmission from entering the uncoated side of the substrate.
- D.** Previously coated surfaces shall be repaired to be relatively free of surface imperfections. A check for loosely held, delaminating coating shall be performed as per ASTM 3359. The gloss shall be dulled by mechanical means to promote proper adhesion of the Sierra Performance Epoxy Acrylic Enamel.
- E.** Satisfactory inspection by the Owner, General Contractor, Project Engineer, at any point in the coating process does not relieve the contractor of ownership and responsibility with regard to application long term service life.

3.03 MIXING AND THINNING

A. MIXING

1. The pigmented components shall be thoroughly mixed to uniform color prior to being combined.

B. THINNING

1. Thinning, when necessary, shall be done with clean, ambient temperature clean, fresh water.
2. Thinning is not normally required for brush, roll application.

3.04 APPLICATION

A. Weather Conditions

1. Apply when air and surface temperatures are between 50-100° F (4.5-38° C), the relative humidity is no greater than 80%, and surface temperature is at least 5° F (3° C) above the dew point.
2. This coating can tolerate application to damp surfaces; however, conditions must be favorable to allow the moisture to evaporate.

3. The Sierra Performance Epoxy Acrylic Enamel shall not be applied, except under shelter, during wet, damp, foggy, or windy weather. When necessary, the area to be coated should be sheltered by a temporary enclosure.

B. Coating Application

1. All smooth bare concrete surfaces should be primed with Sierra Performance Griptec™ Multi-Surface Primer prior to application of Sierra Performance Epoxy Acrylic Enamel.
2. The Sierra Performance Griptec™ Multi-Surface Primer or the Sierra Performance Epoxy Acrylic Enamel shall be recoated no sooner than 1 hour cure.
3. Sags, checks, blisters, skips, teardrops, or rolled edges shall not be accepted and shall be completely removed and recoated.

C. Protection of surfaces

1. The Coating Contractor shall be responsible for protecting all adjacent surfaces from spills, drips, overspray, or any other form of coating damage.
2. The coating contractor and it's subcontractors shall be responsible for removing spots or repairing damaged surfaces to the satisfaction of the project engineer, design architect and/or owner.

D. Clean-up shall be done using soap and clean water.

END OF SECTION