RUST-OLEUM AMERICAN ACCENTS

AMERICAN ACCENTS METALLIC HALF PINTS

DESCRIPTION AND USES

Rust-Oleum® American Accents® Metallic Half Pint enamels are designed to provide long lasting protection and durability. This enamel offers excellent coverage, chip resistance and color retention. For even longer, lasting protection, use American® Accents® Primer first.

PRODUCTS

SKU (8 ounces)	Description
7954730	Metallic Gold
7955730	Metallic Silver

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying.

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. **WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.eps.gov/lead**.**

PRIMING

Use of American® Accents® 7980502 White Primer promotes adhesion and enhances hiding and is especially recommended for bare wood and metal.

APPLICATION

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. Thinning is not required. Avoid painting in direct sunlight or on hot surfaces. Use a good quality synthetic brush. Avoid excessive brushing as this will reduce film thickness and protection. Use light even strokes to ensure smooth and uniform flow.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 1-2 hours, 5-9 hours to handle and can be recoated after 24 hours.

CLEAN-UP

Clean brush and other application tools immediately with mineral spirits.

RUST-OLEUM AMERICAN ACCENTS

TECHNICAL DATA

AMERICAN ACCENTS METALLIC HALF PINTS

PHYSICAL PROPERTIES

		METALLIC HALF PINTS
Resin Type		Hydrocarbon Resin
Pigment Type		Metallic Pastes
Solvents		Mineral Spirits, Stoddard Solvents
Weight	**Per Gallon**	8.1-8.5 lbs.
	Per Liter	0.97-1.02 kg
Solids	**By Weight**	55.9-60.2%
	By Volume	45.0-47.6%
Volatile Organic Compounds		<430 g/l (3.60 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5µ)
Wet Film to Achieve DFT (unthinned material)		3.0-5.0 mils (75-125µ)
Theoretical Coverage at 1 mil DFT (25µ)		47.0 sq.ft./half-pint
Practical Coverage at Recommended DFT (assumes 15% material loss)		15-25 sq.ft./half-pint
Dry Times at 70°F (21°C) and 50% Relative Humidity	**Touch**	2-4 hours
	Handle	5-9 hours
	Recoat	After 24 hours
Dry Heat Resistance		200ºF (93ºC)
Shelf Life		5 years
Flash Point		104°F (40°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM BRANDS

Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877•385•8155
www.rustoleum.com

Form: GDH-165
Rev.: 091013