RUST-OLEUM AMERICAN ACCENTS

AMERICAN ACCENTS CRAFT & HOBBY BRUSH

DESCRIPTION AND USES

Rust-Oleum® American Accents® Craft & Hobby Brush enamels are designed to provide long lasting protection and durability. This enamel offers excellent coverage, chip resistance and color retention. For even longer, lasting protection, use American® Accents® Primer first.

PRODUCTS

SKU (2 oz. jars)	Description
209364	Gloss White
209631	Colonial Red
209633	Gold
209635	Blossom Pink
209636	Silver
209637	Claret Wine
209638	Glow Orange
209640	Semi-Gloss Tranquil Blue
209641	Gloss Black
209642	Gloss Ocean Blue
209643	Nutmeg
209644	Canyon Black
209645	Buttercup
209646	Heirloom White
209647	Blossom White
209648	Hunt Club Green

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying.

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. **WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.eps.gov/lead**.**

PRIMING

Use of American® Accents® 7980502 White Primer promotes adhesion and enhances hiding and is especially recommended for bare wood and metal.

APPLICATION

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. Thinning is not required. Avoid painting in direct sunlight or on hot surfaces. Use a good quality synthetic brush. Avoid excessive brushing as this will reduce film thickness and protection. Use light even strokes to ensure smooth and uniform flow.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 30 minutes, dry to handle in 1 hour, and fully dry in 2-4 hours.

CLEAN-UP

Clean brush and other application tools immediately with soap and water.

RUST-OLEUM AMERICAN ACCENTS

TECHNICAL DATA

AMERICAN ACCENTS CRAFT & HOBBY BRUSH

PHYSICAL PROPERTIES

		CRAFT & HOBBY BRUSH
Resin Type		Water-based Acrylic
Pigment Type		Varies with color
Solvents		Water, Glycol Ethers
Weight	**Per Gallon**	8.6-10.2 lbs.
	Per Liter	1.03-1.22 kg
Solids	**By Weight**	34.1-45.2%
	By Volume	31.6-32.4%
Volatile Organic Compounds		<225 g/l (1.54 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5µ)
Wet Film to Achieve DFT (unthinned material)		4.5-7.5 mils (112.5-187.5µ)
Theoretical Coverage at 1 mil DFT (25µ)		8.1 sq.ft./jar
Practical Coverage at Recommended DFT (assumes 15%		2.0-3.0 sq.ft./jar
Dry Times at 70°F (21°C) and 50% Relative Humidity	**Touch**	30 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		200ºF (93ºC)
Shelf Life		5 years
Flash Point		<200°F (93°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM BRANDS

Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877•385•8155
www.rustoleum.com

Form: CS2896
Rev.: 090613