RUST-OLEUM AMERICAN ACCENTS

TECH DATA SHEET

BRUSH PAINT (Colors & Primers)

DESCRIPTION	An acrylic latex paint in stylish decorative colors. (Metallic colors are alkyds)
USES	Use to beautify and protect wood, metal and a variety of other surfaces.
APPEARANCE	Satin and metallic.
RECOMMENDED PRIMERS	**7**980 White Primer.
PACKAGING	Half-pint (0.24 l) and quarts (0.95 l)
SURFACE PREPARATION	Remove loose paint with a wire brush, scraper or sandpaper. Clean surface with soap and water. For chalky surfaces, scrub with a strong detergent solution. Rinse thoroughly with fresh water and allow to fully dry.
APPLICATION	Apply using brush, roller or spray equipment.
CLEAN-UP	Soap and water for latex, xylene for metallics. Once the product has begun to harden, soap and water may not work and a stronger solvent may be needed.

PHYSICAL PROPERTIES (Calculated values are shown and may vary slightly from the actual manufactured material)

RESIN TYPE	Acrylic latex except for metallics which are solvent based alkyds
SOLVENTS	Water, Propylene Glycol (in the acrylic latex) Xylene, Mineral Spirits (metallic gold and silver)
VOC (Volatile Organic Compounds)	Exempt < 250 g/l (2.1 lb/gal) colors < 450 g/l (3.75 lb/gal) metallic
WEIGHT PER GALLON	8 – 10.5 lb.
WEIGHT PER LITER	0.96 – 1.26 kg
SOLIDS BY WEIGHT	30 – 44 %
SOLIDS BY VOLUME	25 – 31 %
RECOMMENDED DRY FILM THICKNESS PER COAT	1.5 mils (38 µ)
WET FILM TO ACHIEVE DFT	3.5 mils (89 µ)
PRACTICAL COVERAGE @ RECOMMENDED DFT	Approximately 25 sq. ft. (half-pint) (2.3 m²) Approximately 100 sq. ft. (quart) (9.3 m²)

DRY TIMES @70°F (21°C) AND 50% RH		**Primers and colors**	**Metallic finishes**
	TACK FREE	1-2 hours	0.5 – 1 hour
	RECOAT	1- 3 hours	24 hours

DRY HEAT RESISTANCE	200°F (93°C)
SHELF LIFE	3 years. Protect from freezing.

SAFETY (For additional information, see MSDS)

FLASH POINT UNLEADED	200º F (94º F)