



FABRIC & VINYL

DESCRIPTION AND USES

Rust-Oleum® Fabric & Vinyl is a flexible coating that restores color on vinyl, simulated leather and some fabrics. This vinyl coating provides excellent adhesion that will not rub off, crack or peel. It is suitable for use on vinyl furniture, luggage, car seats, car door panels, dashboards, floor mats and other interior surfaces.

PRODUCTS

SKU (4 ounce bottle)	Description
277149	Black
279327	Sand

PRODUCT APPLICATION

PAINTING CONDITIONS

Use when temperature is above 60°F (15°C) and humidity is below 85% to ensure proper drying.

SURFACE PREPARATION

Clean surface with mineral spirits, using a clean cloth to dry the surface. When dry, follow with soap and water, rinse thoroughly and dry with a clean cloth. Mask surrounding area to protect from drips and spills.

PRODUCT APPLICATION (cont.)

APPLICATION

With cap on, shake bottle for one minute. Recap and shake as needed during the painting process. Depress the sponge applicator tip in an inconspicuous area or onto a piece of scrap material to start the paint flow. Apply paint using light pressure on the bottle. For best appearance, apply one thin coat. Let the surface dry thoroughly and then apply two additional coats.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, to handle in 1 hour and is fully dry in 24 hours. Wait at least 6 hours before sitting on or using a painted object.

CLEAN-UP

Drips and spills should be cleaned before paint is dry to the touch. Use water or a rag saturated with rubbing alcohol. Clean sponge applicator by immersing in hot water. Replace the cap tightly and store bottle upright.

NOTE: Do not allow the paint to freeze.



TECHNICAL DATA

FABRIC & VINYL

PHYSICAL PROPERTIES

		FABRIC & VINYL	
Resin Type		Polyurethane	
Pigment Type		Black - Organic	Sand - Organic/Inorganic
Solvents		N-methyl Pyrrolidone, Glycol Ether EP	
Weight	Per Gallon	8.8 lbs.	9.4 lbs.
	Per Liter	1.05 kg	1.13 kg
Solids	By Weight	31.3%	37.2%
	By volume	27.3%	28.9%
Volatile organic Compounds		<250 g/l (2.08 lbs./gal.)	
Recommended Dry Film Thickness (DFT) Per Coat		0.5 mils (12.5μ)	
Wet Film to Achieve DFT		2.0 mils (50μ)	
Practical Coverage at Recommended DFT		13 sq.ft./4 fl. oz.	14 sq.ft./4 fl. oz.
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	15 minutes	
	Handle	30 minutes	
	Recoat	1 hour	
	Full Cure	24 hours	
Dry Heat Resistance		250°F (121°C)	
Shelf Life		6 months	
Flash Point		>200°F (93°C)	
Safety Information		For additional information, see SDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.