AUTOMOTIVE PAINT FOR PLASTIC

DESCRIPTION AND USES

Rust-Oleum® Paint for Plastic renews and revitalizes indoor and outdoor plastics. No primer is required. These sprays are ideal for use on automotive plastics, polypropylene, polystyrene resin, PVC, and fiberglass. Test this product in an inconspicuous area to test for compatibility on the surface. Rust-Oleum® Paint for Plastic features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

248649	Black (12 oz.)
248650	White (12 oz.)
248651	Red (12 oz.)
254855	Clear (11 oz.)
260770	Satin Black (12 oz.)
257389	Silver (12 oz.)

PAINTING APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

For new plastic surfaces, thoroughly wipe down surface with paint thinner to promote adhesion. For aged or weathered surfaces, remove loose material with a brush or scraper, clean with soap and water, rinse and let dry. Sanding may be required for glossy or smooth surfaces. If mildew is present, wash with a bleach solution, rinse and let dry.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart. Maximum adhesion is achieved in 5-7 days. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20-30 minutes, to handle in 1 hour and fully dry in 24 hours. Apply a second coat within 1 hour or after 48 hours.

CLEAN-UP

Wipe off tip when finished. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

TECHNICAL DATA

AUTOMOTIVE PAINT FOR PLASTIC

PHYSICAL PROPERTIES

		PAINT FOR PLASTIC
Resin Type		Modified Alkyd
Pigment Type		Proprietary
MIR		1.40 Max
Fill Weight		11 ounces
Solvents		Acetone and Aromatic Hydrocarbons
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50µ)
Practical Coverage at Recommended DFT		8-10 sq. ft./can (0.90-1.1 m^2/can)
Dry Times at 77°F (25°C) and 50% Rel. Hum.	**Touch**	20 minutes
	Handle	1 hour
	Recoat	24 hours
Shelf Life		5 years
Safety Information	**Flash Point**	-156°F (-104°C)
	Contains	Lead free
	Warning!	**FOR ADDITIONAL INFORMATION, SEE MSDS.**

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM BRANDS

Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877•385•8155
www.rustoleum.com

Form: CS1480
Rev.: 101712