



Rust-Oleum® Engine Enamel - Aerosol

ITEM NUMBERS	#248932 Gloss Black, #248936 Semi-Gloss Black, #248938 Low Gloss Black, #248941 Chevy Orange, #248944 Clear, #248945 Ford Blue, #248947 Chevy Red-Orange, #248948 Ford Red, #248949 Aluminum, #248951 Grabber Green, #248953 Cast Coat Aluminum, #248954 Universal White, #248955 Cast Coat Iron, #248956 Chrysler Industrial Red, #248946 Old Ford Blue, #248957 Chrysler Hemi Orange, #248958 Ford Gray, #248959 Ford Dark Blue, #248960 Daytona Yellow, #248961 GM Blue, #248962 Universal Red
DESCRIPTION	A protective enamel suitable for surfaces that reach temperatures up to 500° F.
USES	For use on automotive engines and automotive surfaces which reach intermittent temperatures of 500°F (260° C).
APPEARANCE	Available in Gloss, Semi-Gloss, Clear and Flat sheens.
PACKAGING	Cast Coat Aluminum, Cast Coat Iron and Clear are available in an 11 oz. aerosol spray can. All other colors are available in a 12 oz aerosol spray can. All aerosol spray cans feature an Any-Angle Spray system that lets you cover hard to reach places, even if the can is sprayed upside-down and also features a Comfort Tip spray nozzle to eliminate finger fatigue.
SURFACE PREPARATION	(See directions on can for more details) Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Clean the surface with soap and water, rinse and let dry. The use of Rust-Oleum® Engine Primer will provide additional adhesion and hiding and is especially recommended for bare metal.
MIXING	Shake can vigorously for one minute after mixing ball begins to rattle. Shake the can often during use.
APPLICATION	Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Avoid spraying in very windy, dusty conditions. Cover the surrounding area to protect from spray mist. Hold the can 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart.

PHYSICAL PROPERTIES (Calculated values, may vary slightly from the actual manufactured material)

RESIN TYPE	Modified alkyd
SOLVENT TYPE:	Ketone/aromatic
VOC (Volatile Organic Compounds)	NA
WEIGHT PER GALLON	NA
WEIGHT PER LITER	NA
SOLIDS BY WEIGHT	13.7 – 27.4%
SOLIDS BY VOLUME	NA
RECOMMENDED DRY FILM THICKNESS PER COAT	1.0 mil
WET FILM TO ACHIEVE DFT	3.0 mils
PRACTICAL COVERAGE @ RECOMMENDED DFT	10 – 15 square feet
APPLICATION CONDITIONS	See above
DRY TIMES @70° - 80°F (21° - 27° C) AND 50%RH	15 minutes tack-free
SHELF LIFE	5 years

SAFETY (For additional information, see MSDS)

FLASHPOINT	156F
LEAD-FREE	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

