



**DECORATIVE
CONCRETE COATING**

DESCRIPTION AND USES

Rust-Oleum® Decorative Concrete Coating is a ready-to-use coating formulated for use on interior or exterior concrete surfaces such as patios, walkways, pool decks, basements and laundry rooms. When applied with the unique Rust-Oleum applicator, Decorative Concrete Coating creates an aesthetic multi-color finish that enhances the appearance of any concrete surface. It is easily applied in one step and provides excellent protection to concrete surfaces. This weather resistant coating resists fading and peeling. Not recommended for use on garage floors or driveways.

PRODUCTS

266551	Sahara
266552	Slate
266554	Sunset

PRODUCT APPLICATION

SURFACE PREPARATION

BARE CONCRETE: Proper surface preparation is critical to performance. Allow new concrete to cure for a minimum of 28 days. Remove any oil spots or spills and wash the floor with EpoxyShield® Heavy-Duty Degreaser (sold separately) or a suitable detergent or degreasing solution and rinse. Then etch the floor using Rust-Oleum® Concrete Etch (sold separately). For best results when using the Concrete Etch, the concrete should be damp, but free of puddles. Mix the entire contents of the Concrete Etch granules with 2 gallons (3.79 l) of water. Use a plastic sprinkling can to evenly distribute the Concrete Etch solution.

Scrub the floor with a stiff bristle brush and make sure the floor stays wet during this process until you are ready to rinse. Continue to scrub while rinsing to ensure all contaminants are washed away. Squeegee off excessive water or puddles and allow to dry completely.

Completely wash, rinse, and squeegee each section before moving on to the next. When all the sections have been completed in this manner, then re-rinse and squeegee the entire floor. When the floor is dry, rub your fingers on the concrete and check for a white film. If a white dust or powder is detected, then repeat the rinsing process being sure to thoroughly scrub during the rinse. Once the concrete is free of surface residue, you are ready to begin application of the coating.

PREVIOUSLY COATED FLOORS: Make sure the floor is clean and dry. Use a wire brush to remove any loose or peeling paint or stain. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. If the floor is sealed, the sealer will have to be removed by grinding or shot blasting. Rinse or sweep away dust and other particles. To ensure proper adhesion, scuff sand the entire surface.

PRODUCT APPLICATION (cont.)

APPLICATION

The Rust-Oleum® applicator tool (sold separately), must be used to apply the Decorative Concrete Coating to ensure proper adhesion and to attain proper texture. Rust-Oleum® Decorative Concrete Coating is ready to use. Do not thin. Apply only when air, material, and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85%. The surface temperature should be at least 5°F (3°C) above the dew point. Thoroughly mix each container to re-disperse any settled pigment. Product may thicken in the can. Stir thoroughly before and during application. If using more than one gallon, intermix (box) all cans of the same product to ensure color uniformity. Do not paint outdoors in direct sunlight or if rain is expected within 48 hours.

Pour a small amount of product directly onto the surface. Apply in 4x4 foot sections, and back roll in the opposite direction to prevent lap marks and to ensure an even coat. Roll slowly and apply light pressure. A single coat can be applied, but a second coat is recommended to provide optimum coverage, durability and abrasion resistance. Note: Painted floors may be slippery when wet.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Allow 2-4 hours between coats. Surface should be ready for foot traffic in 24 hours. For full cure allow 7 days.

CLEAN-UP

Wash tools and equipment with warm water and a mild detergent immediately after use. Properly dispose of all soiled rags and protect unused product from freezing.

COVERAGE

Each gallon covers up to 125 square feet on smooth, bare concrete. Very rough or porous surfaces will require more material.



TECHNICAL DATA

DECORATIVE CONCRETE COATING

PHYSICAL PROPERTIES

		DECORATIVE CONCRETE COATING
Resin Type		Acrylic
Pigment Type		Varies with color, Mica
Solvents		Glycol ethers, Water
Weight	Per Gallon	10.0-10.1 lbs.
	Per Liter	1.26-1.27 kg
Solids	By Weight	45.1-45.4%
	By Volume	44%
Volatile Organic Compounds		<50g/l (0.42 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		5.0-8.0 mils (125-200 μ)
Wet Film to Achieve DFT (Unthinned material)		10.0-15.0 mils (250-375 μ)
Theoretical Coverage at 1 mil DFT (25 μ)		700 sq.ft./gal. (17.2 m ² /l)
Practical Coverage at Recommended DFT (assume 15% material loss)		75-125 sq.ft./gal. (2 coats required)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	2 hours
	Light Foot Traffic	24 hours
	Full Cure	7 days
	Recoat	2-4 hours
Shelf Life		2 years (indoors)
Flash Point		<200°F (93°C)
Safety Information		For additional information, see MSDS
Other Information		Keep from freezing

Calculated values may vary slightly from the actual manufactured material

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877-385-8155
www.rustoleum.com

Form: CS1846
Rev.: 121012