

EPOXYSHIELD BLACKTOP COATING



DESCRIPTION

A long lasting, fast drying coating for renewing and protecting residential asphalt surfaces and driveways. One 2-gallon bucket of Rust-Oleum® Blacktop Coating covers the equivalent of two 5-gallon buckets of conventional asphalt coating.

USES

Use Blacktop Coating to restore the black appearance of driveways and protect the surface from automotive chemicals, de-icing salts and everyday weathering.

APPEARANCE

Dries to a jet black finish.

PACKAGING

EpoxyShield Blacktop Coating comes packaged in a 3-gallon plastic bucket, is filled with 2-gallons of product and has a re-sealable lid.

SURFACE PREPARATION

Clean: Clean the surface making sure it is free of dirt, debris, oil and grease spots. Trim any grass or weeds overgrowing on to the driveway. Using a wire brush or screwdriver, scrape clean all cracks and holes. Remove remaining dirt, dust and debris by sweeping the area with a stiff broom. Heavy grease and oil spots should be cleaned with EpoxyShield Blacktop Cleaner & Degreaser (sold separately). Thoroughly rinse the driveway with fresh water and allow the surface to dry before application.

Repair: Repair major cracks and/or holes in the surface prior to application by using EpoxyShield Blacktop Patch & Crack Filler (sold separately). Follow all directions accordingly.

MIXING

Do not mix or blend this product with any other driveway coating products. Do not dilute.

APPLICATION

After the surface is cleaned and all holes/cracks have been repaired, stir Blacktop Coating thoroughly. If the pavement is extremely hot, apply a fine water mist prior to coating and brush out any remaining water puddles. For edges hard to reach with a roller, trim the edges of the driveway with a brush before applying to the entire surface. Apply coating with a long handled roller in 4' x 4' sections. Cross-roll using perpendicular strokes in each section for better coverage. For faster application, pour the coating out of the bucket directly onto the driveway and use an 18" roller cover to spread. On badly worn asphalt surfaces, a second coat or a ¾" nap roller may be needed. Apply the second coat immediately after the first coat is dry to the touch.

PHYSICAL PROPERTIES (Calculated values, may vary slightly from the actual manufactured material)

RESIN TYPE	Acrylic
SOLVENT TYPE:	Water
VOC (Volatile Organic Compounds)*	46 g/L
WEIGHT PER GALLON*	11.11 lb/gal
WEIGHT PER LITER*	1.33 KG/L
SOLIDS BY WEIGHT*	38.57%
SOLIDS BY VOLUME*	41.13%
PRACTICAL COVERAGE	600 – 800 sq. ft. per bucket
APPLICATION CONDITIONS	50 – 90 degrees F (10 – 32 degrees C) No rain forecasted for 24 hours
POT LIFE @ 50° - 90°F (10° - 32° C)	
DRY TIMES @ 40° - 90°F (4° - 32° C)	
FOOT TRAFFIC	1 hour
VEHICLE TRAFFIC	4 hours
SHELF LIFE	5 years minimum

SAFETY (For additional information, see MSDS)
LEAD-FREE

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM CORPORATION • 11 HAWTHORN PARKWAY • VERNON HILLS, ILLINOIS 60061 • TELEPHONE: 888-683-5667