

• TRUSTED QUALITY SINCE 1921 •

**RUST-OLEUM®**  
SPECIALTY

**SPECIALTY  
FARM EQUIPMENT SPRAYS**

**DESCRIPTION AND USES**

Farm Equipment is a durable, rust preventive enamel that is available in bright original equipment colors. This Stops Rust® formula offers excellent coverage, chip resistance and color retention. Farm Equipment Sprays are ideal for tractors, farm implements, lawn mowers, and more. Not for use on galvanized metal..

**PRODUCTS**

**FINISHES**

7424830	Blue (Ford)
7435830	Green (John Deere)
7443830	Yellow (John Deere)
7449830	Yellow (Caterpillar)
7458830	Orange (Allis Chalmers)
7462830	Red (Massey Ferguson)
7466830	Red (International Harvester)

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

**ALL SURFACES:** Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to thoroughly dry.

**STEEL:** Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated coatings. Use 7769 Rusty Metal Primer for sound rusted or clean metal before application of a finish coat. 7780 Clean Metal Primer is best for clean metal but may be used on sound rusted metal as well.

**PREVIOUSLY COATED:** Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. **LEAD IS TOXIC.** Contact the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (cont.)**

**APPLICATION**

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and the surface temperature is at least 5°F (3°C) above the dew point. The relative humidity should not be greater than 85%. Protect surrounding area from overspray. Overspray can carry a significant distance. Shake can vigorously for one minute after the mixing ball begins to rattle. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. Recoat within 1 hour or after 48 hours; allowing more time in cooler temperatures. **Do not use near open flame.**

**CLEAN-UP**

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

**CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**PHYSICAL PROPERTIES**

		<b>FINISHES</b>
<b>Resin Type</b>		Oil Modified Alkyd
<b>Fill Weight</b>		12 oz.
<b>Volatile Organic Compounds</b>		Maximum 60% by weight
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		Approximately 6-7 sq. ft./can (0.54-0.63 m <sup>2</sup> /can)
<b>Dry Times at 70°F (21°C) and 50% Relative Humidity</b>	<b>Touch</b>	2-4 hours
	<b>Handle</b>	5-9 hours
	<b>Recoat</b>	Within 1 hour or after 48 hours
<b>Dry Heat Resistance</b>		200°F (93°C)
<b>Shelf Life</b>		5 years
<b>Safety Information</b>	<b>Flash Point</b>	Below 0°F (-18°C)
	<b>Contains</b>	Toluene and Xylene
	<b>Warning!</b>	<b>For additional information, see MSDS.</b>

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.