•TRUSTED QUALITY SINCE 1921•

RUST-OLEUM® SPECIALTY

TRIPLE THICK GLAZE

DESCRIPTION AND USES

Triple Thick Glaze is a clear protective coating designed to provide a glass-like clear finish for wood, metal, wicker, plastic, glass, plaster, ceramic and paper. It provides a protective topcoat that applies thicker than other clear coatings. Can be used for indoor or outdoor surfaces.

PRODUCTS

264985 Triple Thick Glaze

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C), or galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

PRIMING

Use of a Painter Touch primer provides excellent adhesion and hiding and is especially recommended for bare wood and metal. The following primers are recommended.

249086 Red Primer
 249088 Gray Primer
 249058 White Primer

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rins e with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile. WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 8-10+from surface and spray in a steady back-andforth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 20 minutes, and can be recoated in 30 minutes.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

1

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

Form: CS1892 Rev.: 121912

RUST-OLEUM° SPECIALTY

TECHNICAL DATA

TRIPLE THICK GLAZE

PHYSICAL PROPERTIES

| Physical Properties | Finishes | |
|---|--|--|
| Resin Type | Acrylic | |
| Pigment Type | NA | |
| MIR | 1.60 Max | |
| Fill Weight | 12 ounces | |
| Solvents | Acetone, Toluene, Ethyl 3-Ethoxypropionate | |
| Wet Film to Achieve DFT | 2 wet coats | |
| Practical Coverage at Recommended DFT (assumes 15% material loss) | 10-12 sq.ft./can. | |
| Dry Times at 77°F (25°C) and 50% Relative Humidity | | |
| Touch | 20 minutes | |
| Handle | 20 minutes | |
| Recoat | 30 minutes | |
| Shelf Life | 5 years | |
| Flash Point | NA | |
| Safety Information | For additional information, see MSDS. | |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Phone: 800•481-4785 www.rustoleum.com Form: CS1892 Rev.: 121912