



## PRIMER Spray and Brush Paints

<b>DESCRIPTION</b>	Rusty Metal Primer 7769 is designed for heavily rusted surfaces only. Clean Metal Primer 7780 is designed for lightly rusted, bare metal or previously painted surfaces. Auto Primers 2067, 2081, 2089 are fast drying and sandable for bare or lightly rusted surfaces. Auto Primers can be used under auto touch-up paints but a test area should be done for compatibility.	
<b>APPEARANCE</b>	Flat red, gray, or white	
<b>RECOMMENDED TOP COATS</b>	Stops Rust® Finishes	
<b>PACKAGING</b>	Aerosols - 12 oz. (340 g) fill weight; 7769 and 7780 also available in half-pint (0.24 l), quart (0.94 l), and gallon (3.79 l)	
<b>SURFACE PREPARATION</b>	Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with commercial detergent or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry.  Scrape and wire brush loose and/or flaking rust or deteriorated coatings. Apply appropriate primer to bare, slightly, or heavily rusted metal.	
<b>APPLICATION</b>	Use in a well ventilated area. Spraying can produce a fog that will travel. Protect surrounding area, clothing and skin from overspray. Shake can vigorously for one minute after the mixing ball begins to rattle. Shake often during use. Hold can upright 12-16 inches for the surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance for the surface and in motion while spraying.	
<b>CLEAN-UP</b>	When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other object into the stem. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.	
<b>PHYSICAL PROPERTIES</b>	(Calculated values are shown and may vary slightly from the actual manufactured material)	
RESIN TYPE	Oil Modified Alkyd	
SOLVENTS	Xylene, Acetone and Aliphatic Hydrocarbon (7769 and 7780 brush versions contain mineral spirits)	
PRACTICAL COVERAGE	Aerosol covers approximately 10-12 sq. ft./ (0.9 – 1.1 m <sup>2</sup> ) Half-pint covers approx. 20-40 sq. ft. (1.9 – 3.7 m <sup>2</sup> ) Quart covers approx. 60-80 sq. ft. (5.6 – 7.4 m <sup>2</sup> ) Gallon covers approx. 250-300 sq. ft. (23.2 – 27.9 m <sup>2</sup> )	
DRY TIMES @70°F (21°C) and 50% RH	<u>Spray</u>	<u>Brush</u>
	Touch	2-4 hours
	Handle	5-9 hours
	Recoat	after 24 hours
	Anytime for the Auto Primers	
VOLATILE ORGANIC COMPOUND	<60% Aerosol; <450 g/l Gallon Half-Pint and Quart are exempt	
SHELF LIFE	5 years	
FLASH POINT	-156° F (-144° C)	104° F (40° C)
LEAD FREE		