TECH DATA SHEET

# PREMIUM WOOD CONDITIONER – Gallon & Quart

| | |
|---|---|
| DESCRIPTION | A unique high solids, oil-based wood conditioner designed to penetrate deeply into wood to provide more even color and better stain control for all wood projects. |
| PRODUCT CODE | Gallon #211774, Quart #211775 |
| EXPOSURE | Interior use only |
| PRODUCT TYPE | Stain |
| SURFACE TYPE | Wood furniture, cabinets, doors & trim, floors and paneling. |
| PACKAGING | Gallon (3.79 liters), Quart (.9 liters) |
| SURFACE PREPARATION | For previously finished wood, first remove the old coating by sanding or stripping to bare wood. To prepare bare wood for conditioning, begin by sanding in the direction of the grain. Begin with #120 grit sandpaper and progress through #150, #180, and #220 grit.<br><br>Before conditioning the wood, remove all sanding dust using a tack-cloth, a rag lightly dampened with mineral spirits, or vacuum. Make sure the wood surface is dry, clean, and free of dust, dirt, grease or glue before conditioning and staining. |
| APPLICATION | Stir the contents thoroughly before use. Apply Varathane Premium Wood Conditioner with a brush or clean, lint-free cloth. For best results, apply the conditioner across the grain until the wood is saturated on top. Wipe the excess wood conditioner off in the direction of the wood grain. Do not let the conditioner dry before wiping the excess. Allow the conditioner to penetrate for 30 minutes before staining. Apply at temperatures above 55° F (13° C) and below 90°F (32° C). |
| PROTECTING YOUR WOOD | For best results, stain your project with Varathane Oil-based Premium Wood Stains. NOTE: Varathane Oil-based Premium Wood Conditioner is not recommended for use with water-based stains. |
| CLEAN-UP | Use mineral spirits or paint thinner. |

**PHYSICAL PROPERTIES** (Calculated values, may vary slightly from the actual manufactured material)

| | |
|---|---|
| RESIN TYPE | Modified Alkyd |
| WEIGHT per GALLON | 7.0 lbs (3.2 kg) |
| SOLIDS by WEIGHT<br>SOLIDS by VOLUME | 37.4%<br>32.4% |
| PRACTICAL COVERAGE | Gallon: Approximately 600 square feet. Quart: Approximately 150 square feet. Coverage may vary depending on the applicator and wood species used. |
| VOC | < 550 g/l (4.6 lb/gal) |
| DRY TIMES @ 70°F (21°C) and 50% RH | Touch 2 hours<br>Handle 4-6 hours<br>Recoat 30 minutes before applying stain coat. |
| SHELF LIFE | 3 years |

SAFETY

| | |
|---|---|
| FLASHPOINT | 106º F (41º C) |
| LEADFREE | |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM CORPORATION • 11 HAWTHORN PARKWAY • VERNON HILLS, ILLINOIS 60061 • TELEPHONE: 888-683-5667

An RPM Company

Published 12/08