



**MARTIN MATHYS  
PEGANOX**

**DESCRIPTION AND USES**

Peganox is a single component, high build, self priming, rust preventative water-based acrylic elastomeric coating. Peganox is designed for use on minimally prepared sound rusted or clean steel in mild to moderate industrial environments. Two coats are required.

**APPEARANCE**

Satin

**PRODUCTS**

SKU	Description
225321	White
225322	Off White
225323	Green Gray
225324	Black

**PACKAGING**

5-kg pails.

**RECOMMENDED PRIMERS**

Peganox is self-priming when applied to minimally prepared Sound rusted or clean steel. Use one of the following primers on very smooth and non-ferrous substrates.

SKU	Description
3202502	3200 System Clear Blue Undercoat
202600	Pegalink

**COMPATIBLE TOPCOATS**

A topcoat is optional.

High Performance 3700 System DTM Acrylic Enamel  
Industrial Choice® 5200 System DTM Acrylic  
Sierra Performance™ S-37 Metalmax

**COVERAGE**

One pail of Peganox will cover approximately 250 square feet at 3 mils (75µ) dry film thickness

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

**ALL SURFACES:** Remove all dirt, grease, oil, salt or other contaminants by washing the surface with 3599 Industrial Pure Strength® Cleaner/Degreaser, detergent, or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry. Thoroughly cured, hard or glossy previous coatings which are very smooth may require scuff sanding to maximize adhesion.

Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove loose rust, scale and deteriorated coatings to obtain a sound rusted surface. A rusted surface is considered to be sound when rust can no further be removed by scraping the surface by hand using a dull putty knife under moderate pressure.

**PRODUCT APPLICATION (cont.)**

The surface may also be prepared by the use of High Pressure Water Jetting (HPWJ) in accordance to SSPC-SP-12/NACE 5 to a Visual Surface Preparation Condition of WJ-4.

**PRIMING**

Normally not required. Exceptions include:  
New galvanized steel: Prime with 3202 Clear Blue Undercoat  
Smooth metals: Prime with Pegalink

**APPLICATION**

Apply only when air and surface temperatures are between 46-130°F (8-55°C) and surface is at least 5°F (3°C) above dew point. The relative humidity should not be greater than 80%. The published recoat time may be extended when the relative humidity is greater than 70%. A minimum of two coats are required for a total minimum dry film thickness of 6 mils, (150µ).

**THINNING**

Normally not required. Thin 3% with clean fresh water when Applying by airless spray and 5% when applying by air atomized spray.

**CLEAN UP**

Water. Use 3599 Industrial Pure Strength Cleaner/Degreaser or soap and water if material begins to dry.

**EQUIPMENT RECOMMENDATIONS**

**BRUSH:** Use a good quality synthetic bristle.

**ROLLER:** Use a good quality synthetic ¾" nap roller cover.

**AIR ATOMIZED SPRAY:**

Method	Fluid Tip	Fluid Delivery	Atomizing Pressure
<b>Pressure</b>	0.055-.0700	8-12 oz./min.	25-50 psi
<b>Siphon</b>	0.055-.0700	-----	35-60 psi
<b>HVLP (var.)</b>	0.043-.0700	-----	10 psi at tip

**AIRLESS SPRAY:**

Fluid Pressure	Fluid Tip	Filter Mesh	2,500
psi (min)	0.013-0.017	60	



**PHYSICAL PROPERTIES**

Physical Properties		PEGANOX
Resin Type		Water-based Acrylic Elastomeric
Pigment Types		Titanium Dioxide, Zinc Phosphate
Solvents		Water, Ethylene Glycol
Weight	Per Gallon	10.0-10.5 lbs.
	Per Liter	1.2-1.3 kg
Solids	Weight	53.0 ± 3%
	Volume	48.0 ± 3%
Volatile Organic Compounds		25 g/l (0.21 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		3.0 mils (75µ) – 2 coats are required
Wet Film to Achieve DFT		6.5 mils (162.5µ)
Theoretical Coverage at 1 mil (25µ) DFT		770 sq.ft./gal. (18.9 m <sup>2</sup> /l)
Practical Coverage at Recommended DFT (assumes 15% material loss)		220 sq.ft./gal. (5.4 m <sup>2</sup> /gal.)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Tack Free	1 hour
	Handle	2-3 hours
	Recoat	6 hours
	Full Cure	14 days
Elasticity at 70°F (21°C)		200%
Shelf Life		4 years in unopened containers properly stored in a cool dry area. Do not allow to freeze.
Flash Point		>200°F (93°C)
Safety Information		WARNING! HARMFUL OR FATAL IF SWALLOWED. MAY CAUSE RESPIRATORY TRACT, EYE AND SKIN IRRITATION. MAY CAUSE ALLERGIC SKIN REACTION. FOR INDUSTRIAL OR COMMERCIAL USE ONLY. NOT INTENDED FOR RESIDENTIAL USE. KEEP OUT OF REACH OF CHILDREN. REFER TO PRODUCT MATERIAL SAFETY DATA SHEET (MSDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.