RUST-OLEUM

DRY GRAPHITE

DESCRIPTION AND USES

Rust-Oleum® Dry Graphite iprovides long lasting lubrication that bonds quickly to any clean metal, wood, concrete or plastic surface. The dry graphite will not pick up dust, dirt, mud or grime with excellent resistance to rain, snow, and heat. Suitable for use in operating temperature range of -80° to 1060°F and will effectively lubricate loads up to 18,000 psi.

For Professional Use Only.

FEATURES

- Non staining
- Does not attract dirt or dust
- Convenient aerosol with 360º spray tip

PRODUCTS

SKU	Container Size
273925	11 oz fill weight aerosol
274835	11 oz fill weight aerosol (Canada only)

PRODUCT APPLICATION

SURFACE PREPARATION

Surfaces must be dry and free of grease, oil, dirt, rust, wax, or other forms of surface contamination

APPLICATION

Use in a well ventilated area when temperatures are between 50 -90ºF (10-32ºC). Avoid spraying in very windy and dusty conditions.

Shake well before and during use. Hold can 10-16" from the surface and spray in a steady back-and-forth motion and apply an even, uniform film on all metal surfaces requiring lubrication. Repeat as necessary.

PRECAUTION

Vapors may ignite explosively. Keep away from heat, sparks and flame. Extinguish all flames and pilot lights, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Prevent buildup of vapors by opening all windows and doors to achieve cross ventilation. Avoid contact with eyes and skin.

CLEAN UP

Properly dispose of container and unused contents in accordance with local, state and federal regulations.

STORAGE

Store in cool dry areas and protect from excessive heat.

TECHNICAL DATA

DRY GRAPHITE

PHYSICAL PROPERTIES

	Dry Graphite
Solvent	Naphtha, Isopropyl Alcohol, N-butanol
Fill Weight	11 ounces
Shelf Life	5 years
Flash Point	-141ºF (-96ºC)
Safety information	For additional information, see MSDS.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM INDUSTRIAL BRANDS

Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877•385•8155
www.rustoleum.com/industrial

Form: GDH-47
Rev.: 081313