RUST-OLEUM® COMMERCIAL

C580 SYSTEM COMMERCIAL LATEX

DESCRIPTION AND USES

Rust-Oleum® General Purpose Latex Paint is especially formulated to provide a high-hiding, uniform finish with excellent touch-up qualities when properly applied on interior walls and ceilings. This product features high hiding, excellent touch-up, burnish resistance, low VOC and easy soap and water clean-up.

PRODUCTS

FINISHES

1-Gallon	5-Gallon	Description
262608	263657	Bright White Eggshell
262610	263662	Bright White Semi-Gloss
262613	263655	Antique White Eggshell
262614	263661	Antique White Semi-Gloss
262615	263659	Linen White Eggshell
262616	263665	Linen White Semi-Gloss

PACKAGING

One gallon containers and five gallon pails

PRODUCTS APPLICATION

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, grease, wax, dust, chalk, rust or any other contaminants that may prevent proper adhesion. Remove all loose or peeling paint. Glossy surfaces must be dulled by sanding. Patch all holes and cracks with appropriate patching compound and sand smooth. Plaster, concrete block, concrete and masonry surfaces must be cured. Remove all form release and curing agents. If the surface has a pH of 8 or higher, the surface must be primed with Zinsser® Bulls Eye 1-2-3® Primer or an equivalent alkali resistant primer.

APPLICATION

Mix thoroughly before use. Apply only when air, surface, and material temperatures are between 50-90°F (10-32°C), surface is at least 5°F above the dew point and relative humidity is below 85% during and after application. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively.

THINNING

Not normally required. If needed, thin with clean fresh water. Thinning should not exceed 10% by volume.

CLEAN-UP

Soap and water.

PERFORMANCE CHARACTERISTICS

Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.

RUST-OLEUM® COMMERCIAL

TECHNICAL DATA

C580 SYSTEM COMMERCIAL LATEX

PHYSICAL PROPERTIES

		EGGSHELL FINISHES	SEMI-GLOSS FINISHES
Resin Type		Ethylene Vinyl Acetate	Ethylene Vinyl Acetate
Pigment Type		Titanium dioxide and extenders	Titanium dioxide and extenders
Solvents		Water	Water
Weight	**Per Gallon**	10.6-10.7 lbs.	10.2-10.3 lbs.
	Per Liter	1.27-1.28 kg	1.22-1.23 kg
Solids	**By Weight**	41-45%	39-43%
	By Volume	28-32%	28-32%
Volatile Organic Compounds		<150 g/l (1.25 lbs./gal.)	<150 g/l (1.25 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50µ)	1.0-2.0 mils (25-50µ)
Wet Film to Achieve DFT (unthinned material)		3.5-6.0 mils (87.5-150µ)	3.5-6.0 mils (87.5-150µ)
Theoretical Coverage at 1 mil DFT (25µ)		450-515 sq.ft./gal. (11.1-12.7 m^2/l)	450-515 sq.ft./gal. (11.1-12.7 m^2/l)
Practical Coverage at Recommended DFT (assumes 15% material loss)		190-435 sq.ft./gal. (4.7-10.7 m^2/l)	190-435 sq.ft./gal. (4.7-10.7 m^2/l)
Dry Times at 77°F (25°C) and 50% Relative Humidity	**Touch**	1 hour	1 hour
	Recoat	4-6 hours	4-6 hours
Shelf Life		5 years	5 years
Safety Information	**Contains**	No lead has been deliberately added.	
	WARNING!	**FOR INDUSTRIAL OR COMMERCIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. REFER TO MATERIAL SAFETY DATA SHEET (MSDS) AND LABEL FOR ADDITIONAL SAFETY INFORMATION.**	

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

RUST-OLEUM® INDUSTRIAL BRANDS

Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877•385•8155
www.rustoleum.com/industrial

Form: 3003990
Rev.: 110811