



ZINSSER® B-I-N® SHELLAC BASED PRIMER (SPRAY)

DESCRIPTION AND USES

Zinsser® B-I-N® Shellac-Based Primer is a primer-sealer, stain blocker recommended for almost all surfaces. It blocks grease spots, fire, smoke, water stains, ink, crayon, knots and sap streak stains and seals odors resulting from water and fire damage. It seals knots, porous wood and spackled areas. It sticks to ceramic tile, glass, metal, plastic and hardboard.

Use to prime picture frames, stools, benches, arts & crafts, wicker & louvers and more.

FOR INTERIOR USE ONLY.

PRODUCT

| SKU | DESCRIPTION |
|------|----------------|
| 1008 | 13 Oz. Aerosol |

PRODUCT APPLICATION

SURFACE PREPARATION

Surfaces should be clean, dry, sound and free of dust, dirt, grime, grease, oil, wax, wallpaper adhesive or any contamination that may interfere with adhesion. Remove loose paint, dirt and rust. Mask off nearby objects.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply at room temperature of 70°F in a well ventilated area. Avoid high humidity. Shake can vigorously until the agitator ball inside the can rattles. If the ball does not rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Turn the can upside down and continue shaking for one minute. Shake occasionally during use. Spray 10-12" from object with short 'dusting' strokes.

DRY TIME

At normal temperatures, B-I-N will dry to the touch in 15 minutes and surfaces can be painted in 30 minutes.

CLEAN-UP

Wipe off tip before storing. Clean up wet paint with mineral spirits. Throw away empty can in garbage pickup. Do not burn or puncture the can, even when empty.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into the stem.

| | | |
|-----------------------------------------------------------------------------------|-----------------------------------------------------|---------------|
| | TECHNICAL DATA | BIN-08 |
|  | ZINSSER® B-I-N® SHELLAC BASED PRIMER (SPRAY) | |

PHYSICAL PROPERTIES

| SHELLAC-BASED PRIMER SPRAY | | |
|------------------------------------------------------------------|--------|---------------------------------------------------------------------------------------------------------|
| Resin Type | | Shellac-Based |
| Pigment Type | | Titanium Dioxide, Aluminum Silicate, Mica |
| Solvents | | Acetone, Ethanol, N-Butanol |
| MIR | | 1.00 Max |
| Fill Weight | | 13 ounces |
| Recommended Dry Film Thickness (DFT) per Coat | | 1.5-2.5 mils (37.5-62.5μ) |
| Practical Coverage at Recommended DFT (assume 15% material loss) | | 10-12 sq. ft./can (0.9-1.1 m ² /can) depending on application method and surface porosity |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch | 15 minutes |
| | Recoat | 30 minutes |
| Shelf Life | | 5 years |
| Flash Point | | -156°F (104°C) |
| Safety Information | | For additional information, see SDS |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.