

	TECHNICAL DATA	ROC-108
• TRUSTED QUALITY SINCE 1921 • 	RUST-OLEUM® CLEAR FINISH FLOOR TOPCOAT	

DESCRIPTION AND USES

Rust-Oleum® Clear Finish Floor Topcoat is a ready-to-use interior/exterior concrete clear protective coating formulated for use on garages, carports, driveways, basements, porches, patios, walkways and pool decks. This clear topcoat is available in 3 finishes: Gloss, Matte and Satin Textured. This product is designed for use over bare concrete or over 1-part epoxy floor paints such as Rust-Oleum Concrete & Garage Floor Paint + Primer to add a protective, finish that resists damage from hot tires, motor oil, grease and gasoline. The durable, UV and weather resistant finish is easy to maintain and resists fading and peeling. It can be easily cleaned up with soap and water.

NOTE: Not recommended for use on asphalt surfaces.

PRODUCT FEATURES

- Water-based acrylic
- Hot tire and chemical resistant
- For use on garages, driveways, patios and basements

PRODUCTS

SKU	DESCRIPTION (1 Gallon)
320202	Gloss Clear Finish Floor Topcoat
380895	Matte Clear Finish Floor Topcoat
380896	Satin Textured Clear Finish Floor Topcoat

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Whether over bare or freshly coated concrete: Proper surface preparation is critical to performance. Allow new concrete to cure for a minimum of 28 days. Before coating, if necessary, use a wire brush or sander to remove any loose or unsound concrete or masonry. Remove grease, oil, salt and other contaminants with Rust-Oleum Heavy-Duty Degreaser or Rust-Oleum Cleaner & Degreaser (sold separately). Scrub spots thoroughly with a stiff bristle brush or broom and wipe up excess cleaner with rags or paper towels to keep contaminants from spreading. Rinse thoroughly with fresh water. Repeat as necessary until completely clean.

Bare Concrete Surfaces: For proper penetration and maximum adhesion, use Rust-Oleum Concrete Etch or Rust-Oleum Clean & Etch (sold separately). Follow label instructions carefully and allow the floor to dry completely. Wipe your fingers over the clean, dry surface. If you see any dust or powder on your fingers, repeat scrubbing and rinsing until the floor is clean.

For freshly painted surfaces: Apply over 1-part epoxy water base paints and stains such as Rust-Oleum Concrete & Garage Floor Paint + Primer as a protective clear topcoat without further surface preparation. Apply topcoat after 24 hours of base coat application and within 7 days.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Rust-Oleum Clear Finish Floor Topcoat is ready to use. Do not thin. Apply only when air (ambient) temperature is between 50-90°F (10-32°C) and the relative humidity is below 85%. Do not paint outdoors if rain is expected within 48 hours. **NOTE:** Painted floors may be slippery when wet. If desired, mix in Rust-Oleum Anti-Skid Additive (sold separately).

Stir thoroughly before applying. Use a brush or edger to trim the perimeter and hard-to-reach areas. Use a long handled extension pole and a high quality $\frac{3}{8}$ " nap roller cover to apply an even coat of Rust-Oleum Clear Finish Floor Topcoat onto the surface. Apply in 4'x4' foot sections and maintain a wet edge to prevent lap marks and gloss differences. Continue applying in 4'x4' sections until complete. Only one coat is necessary. If a second coat is desired, wait 4 hours before applying the second coat in a direction perpendicular to the first. A second coat is recommended when applying over bare concrete. Occasional touch-up may be necessary for areas subject to heavy vehicle traffic.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Dry times increase at cooler temperatures. The surface should be ready for light foot traffic in 24 hours. **FOR FULL CURE AND VEHICLE TRAFFIC, ALLOW 5 DAYS.**

CLEAN-UP

Wash tools and equipment with warm water and a mild detergent immediately after use. Properly dispose of all soiled rags and protect unused product from freezing.

COVERAGE

Each gallon contains enough material to cover approximately 150-250 square feet over bare concrete and 300-400 square feet over coated concrete. Additional product may be required depending on surface conditions.

	TECHNICAL DATA	ROC-108
• TRUSTED QUALITY SINCE 1921 • RUST-OLEUM®	RUST-OLEUM® CLEAR FINISH FLOOR TOPCOAT	

PHYSICAL PROPERTIES

		CLEAR FINISH FLOOR TOPCOAT
Resin Type		Acrylic
Pigment Type		NA
Solvents		Water; Glycol Ethers
Weight	Per Gallon	8.5-8.6 lbs.
	Per Liter	1.02-1.03 kg
Solids	By Weight	26.2-27.3%
	By Volume	24.4-25.3%
Volatile Organic Compounds		<50 g/L
Recommended Dry Film Thickness (DFT)		1.5-2.5 mils over bare concrete 1.0-1.5 mils over coated concrete
Wet Film to Achieve DFT (unthinned material)		5.5-10.5 mils over bare concrete 4.0-5.5 mils over coated concrete
Practical Coverage at Recommended DFT		Approximately 150-250 sq. ft. over bare concrete Approximately 300-400 sq. ft. over coated concrete
Dry Times at 77°F (25°C) and 50% Relative Humidity	Dry to Touch	3-4 hours
	Recoat	4 hours
	Light Foot Traffic	24 hours
	Full Cure	5 days
Shelf Life		3 years
Flash Point		>200°F (93°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.