



WATCO® BUTCHER BLOCK OIL + STAIN

DESCRIPTION AND USES

Watco® Butcher Block Oil + Stain is specially formulated for use on wooden butcher blocks, cutting boards, salad bowls and other wood applications which require a food safe finish. Easy to apply and maintain, it is nontoxic and safe for food contact when fully dried (meets government standards of 21CFR 175.300). More durable than traditional butcher block oils, Watco Butcher Block Oil + Stain provides a rich lustrous color and sheen while actually protecting your wood surfaces.

Recommended Uses: Butcher Blocks, Wooden Bowls, Utensils, and Furniture.

PRODUCTS

SKU	DESCRIPTION (Half Pint)
359023	Ebony
359024	Hazelnut

PRODUCT APPLICATION

SURFACE PREPARATION

To maintain Watco Butcher Block Oil + Stain nontoxicity and food safety, apply the finish over raw wood. Prepare the wood for finishing by sanding with #150 and #220 grit sandpaper in the direction of the grain.

Before applying oil, remove all grease, glue, or wax and vacuum all sanding dust and dirt.

PRODUCT APPLICATION (cont.)

APPLICATION

Watco Butcher Block Oil & Finish is a ready-to-use product. Do not thin. Use only at room temperature. Mix material thoroughly before application. Stir occasionally during use. Apply with a soft, clean cloth. Allow 6 hours dry time before re-coating. Prior to re-coating, lightly scuff sand with #400 grit sandpaper. Allow 72 hours prior to normal use. Hand wash surface prior to contact with food. DO NOT WASH IN DISHWASHER. If desired, use additional coats to build a finish. Do not apply over other finishes. When used on objects with small openings, such as canisters, proper drying may be inhibited when applied on interior surface.

CLEAN UP

Application tools or brushes should be cleaned with mineral spirits.

	TECHNICAL DATA	WAT-22
	WATCO® BUTCHER BLOCK OIL + STAIN	

PHYSICAL PROPERTIES

		WATCO BUTCHER BLOCK OIL + STAIN
Resin Type		Tung Oil Alkyd
Pigment Type		Varies on color
Solvents		Mineral Spirits
Weight	Per Gallon	7.7 lbs.
	Per Liter	0.93 kg
Solids	By Weight	39.4%
	By Volume	30.4%
Volatile Organic Compounds		<560g/l
Recommended Dry Film Thickness (DFT) per Coat		NA
Practical Coverage (assume 15% material loss)		Varies with type and porosity of wood
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	2 hours
	Recoat	6 hours
	Full Cure	72 hours
Shelf Life		3 years
Flash Point		150°F (40°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 800-901-0411
www.rustoleum.com

Form: ARJ-2086
Rev.: 110822