



**PEEL COAT®
LENS TINT**

DESCRIPTION AND USES

Rust-Oleum® Peel Coat® Lens Tint is an easy, no-commitment way to customize your vehicle tail lights, fog lights and turn indicators. This translucent coating gives you lights a “black-out” appearance until they are lit; then the original color shows through. Lens Tint creates a finish that is durable and weather resistant. Just spray it on, keep it on and peel it off when ready.

PRODUCTS

| SKU | DESCRIPTION (Aerosol) |
|--------|-----------------------|
| 297622 | Translucent Black |
| 340422 | Translucent Yellow |

PRODUCT APPLICATION

SURFACE PREPARATION

Removing the lens from your vehicle is recommended for ease of application. If you cannot remove the lens from your vehicle, mask the adjoining areas to protect from spray mist. Prepare the surface by removing any oil, grease, wax or road tar. Thoroughly wash the surface with soap and water prior to application. Rinse with fresh water and allow to dry. Priming is not required or recommended.

PAINTING CONDITIONS

Use outdoors or in a well ventilated area. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 8-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Apply 2-3 light coats to build the desired film thickness, followed by one coat to achieve a smooth final film. DO NOT APPLY MORE THAN 4 COATS. Remove any tape while the last coat is still wet. Allow coating to dry to a matte finish (about 5 minutes) between coats. Allow the coating to cure for 24 hours before washing. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Lens Tint dries to the touch in 20 minutes, to handle in 1 hour and is fully cured in 24 hours.

REMOVAL


You can peel film off once the coating has fully cured. A microfiber cloth or mineral spirits can assist in the removal of film in intricate areas. This coating has been formulated for temporary use and is recommended to be removed within 6 months or less.

CLEAN-UP

When finished spraying, clear the spray valve by turning can upside down and pushing the button for 5 seconds. Allow wet paint to dry. Once dry, peel away or clean up with mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

| | | |
|---|-----------------------|---------------|
|  | TECHNICAL DATA | PCG-05 |
| PEEL COAT[®] | | |
| LENS TINT | | |

PHYSICAL PROPERTIES

| | | PEEL COAT LENS TINT |
|---|--------------------|---|
| Resin Type | | Synthetic Rubber |
| Pigment Type | | Varies with color |
| Solvents | | Blend of Aliphatic and Aromatic Solvents |
| MIR | | 1.60 Max |
| Fill Weight | | 10 ounces |
| Recommended Dry Film Thickness (DFT) Per Coat | | 0.5-1.0 mils (12.5-25 μ) |
| Practical Coverage at Recommended DFT | | 8.0 sq. ft./can (0.75 m ² /can) |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch | 20 minutes |
| | Handle | 1 hour |
| | Fully Cured | 24 hours |
| Shelf Life | | 2 years |
| Flash Point | | -140°F (-96°C) |
| Safety Information | | For additional information, see SDS |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.