



RUST-OLEUM® SPECIALTY FLUORESCENT SPRAYS

DESCRIPTION AND USES

Rust-Oleum® Specialty Fluorescent provides bright, highly visible color on a variety of surfaces. It is ideal for interior and exterior projects and also glows under a black light. For best results, apply over a white basecoat.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
1932830	Fluorescent Green
1942830	Fluorescent Yellow
1954830	Fluorescent Orange
1955830	Fluorescent Red Orange
1959830	Fluorescent Pink

PRODUCT APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Rust-Oleum primer provides excellent adhesion and hiding and is especially recommended for bare wood and metal. Apply an undercoat of white primer on darker surfaces for maximum brilliance.

APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. Shake often during use. If mixing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Hold can upright 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. May recoat at anytime. Dries to the touch in 15 minutes and to handle in 1/2 hour. Fully dry in 24 hours. May top coat at anytime.

CLEAN-UP

When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. Clean up wet paint with xylol or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



**RUST-OLEUM® SPECIALTY
FLUORESCENT SPRAYS**

PHYSICAL PROPERTIES

		FLUORESCENT SPRAYS
Resin Type		Modified Acrylic Lacquer
Pigment Type		Varies with color
Solvents		Acetone, Hexane, Toluene, Xylene
MIR		1.30 Max
Fill Weight		11 ounces
Practical Coverage (assumes 15% material loss)		Approximately 10-12 sq. ft./can (0.9-1.09 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	15 minutes
	Fully Dry	24 hours
	Recoat	Anytime
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

