



# RUST-OLEUM® CHALKBOARD SPRAY

## DESCRIPTION AND USES

Rust-Oleum® Chalkboard is an ultra-hard, scratch resistant, flat finish that allows you to create a unique writable-erasable surface. Ideal for use on doors, tables, cabinets, picture frames, flower pots and more. Can be applied to wood, metal, glass, terra cotta, paperboard and hardboard. It's also great for resurfacing ping pong tables.

## PRODUCTS

SKU	DESCRIPTION (Aerosol)
1913830	Black Chalkboard
302487	Clear Chalkboard

## PRODUCT APPLICATION

### SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### PRIMING

Use of a Rust-Oleum primer provides excellent adhesion and hiding and is especially recommended for bare wood, bare metal, paperboard and hardboard.

## PRODUCT APPLICATION (cont.)

### APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart. **Do not use near open flame.**

When fully dry, (24 hours) prepare the surface for use by rubbing the side of chalk over the entire surface. Erase and the chalkboard is ready for use. For best results, use only calcium carbonate chalk and felt erasers. Other chalks will scratch the surface.

### DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, to handle in 1 hour and fully dry in 24 hours. Apply a second coat within 1 hour or after 24 hours.

### CLEAN-UP

When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. Clean up wet paint with xylol or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

### CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	<b>TECHNICAL DATA</b>	<b>SPC-03</b>
<small>• TRUSTED QUALITY SINCE 1921 •</small> <b>RUST-OLEUM®</b> SPECIALTY	<b>RUST-OLEUM®</b> <b>CHALKBOARD SPRAY</b>	

**PHYSICAL PROPERTIES**

		CHALKBOARD SPRAY
<b>Resin Type</b>		Acrylic Modified Alkyd
<b>Pigment Type</b>		Carbon Black (1913830), Silica (302487)
<b>Solvents</b>		Acetone, Mineral Spirits, VM&P Naptha, Xylene
<b>MIR</b>		0.80 Max
<b>Fill Weight</b>		11 ounces
<b>Practical Coverage (assume 15% material loss)</b>		Approximately 7 sq. ft./can (0.63 m <sup>2</sup> /can)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Tack Free</b>	20 minutes
	<b>Handle</b>	1 hour
	<b>Recoat</b>	Within 1 hour or after 24 hours
<b>Dry Heat Resistance</b>		200°F (93°C)
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		-156°F (-104°C)
<b>Safety Information</b>		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.