



# RUST-OLEUM HOME<sup>®</sup> FLOOR COATING KITS

## DESCRIPTION AND USES

Rust-Oleum HOME<sup>®</sup> Floor Coating is an extremely durable, easy to use, revolutionary technology that allows you to coat over a wide variety of substrates inside the home without stripping, sanding or priming. Transform any room by revamping your outdated floor - simply clean, apply the required Base Coat + Top Coat system for a brand new look to your space.

For use on any bare, stained, sealed or previously coated surfaces such as ceramic tile, porcelain tile, concrete, hard wood, laminate, vinyl and linoleum.

Great for laundry rooms, basements, kitchens, bathrooms, and more.

## PRODUCT FEATURES

- 2 Step System
- No stripping, sanding or priming
- Superior adhesion to tough surfaces
- Maximum scratch and stain resistance
- Walk on in one day

## PRODUCTS

| SKU    | DESCRIPTION (Kit)                           |
|--------|---|
| 360098 | HOME White Tint Base Matte Kit              |
| 360099 | HOME White Tint Base Semi-Gloss Kit         |
| 360100 | HOME Deep Tint Base Matte Kit               |
| 360101 | HOME Deep Tint Base Semi-Gloss Kit          |
| 384958 | HOME White Tint Base Anti-Slip Textured Kit |

## KIT CONTENTS

- 1-Quart Floor Base Coat
- 1-Quart Floor Top Coat
- 1-4 oz. Heavy-Duty Cleaner

**NOTE:** White Tint Base can be applied as is for Ultra White or tinted prior to application. Two base coats are required when applying the White Tint Base in Ultra White. Deep Tint Base must be tinted prior to application.

## OTHER SUPPLIES NEEDED (not included in kit)

- 3/8" Nap Roller Sleeve
- 1/4" Nap Roller Sleeve
- Roller Frame
- Roller Pan
- Painter's Tape
- Paint Tray

## PRODUCT APPLICATION

### READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

**IMPORTANT:** All flooring should be tested for adhesion before coating the entire floor. Clean a small 3"x3", inconspicuous area, let dry. Apply base coat over area and allow to dry for 12 hours. Take a utility knife and make an X in the coating down to the flooring. Apply a 4" piece of duct tape over the X and press firmly. Remove the tape with one quick pull. If more than 10% of the coating comes off, the floor will need to be sanded with 60-80 grit sandpaper before coating the entire floor.

### SURFACE PREPARATION

Rinse or sweep away any dirt and dust. Clean the entire floor with a cleaner degreaser, such as Original Krud Kutter<sup>®</sup> Cleaner Degreaser, or provided cleaner. Rinse thoroughly and allow to dry completely. For any areas where caulk is present, caulk needs to be removed before applying coating. For waxed floors, wax needs to be removed before applying coating.

**NOTE:** Failure to follow this preparation method may result in poor adhesion and possible coating failure.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### APPLICATION

Rust-Oleum HOME<sup>®</sup> Base Coat is ready to use. Do not thin. Stir thoroughly prior to use. If using more than one can of Base Coat, intermix cans together for color uniformity. Apply when air, material, and surface temperatures are between 50-90°F (10-32°C) and relative humidity is below 85%. Use a high quality bristle brush or edger to trim the perimeter and hard-to-reach areas. Use a long handled roller and a high-quality, 3/8" (Base Coat) and 1/4" (Top Coat) nap roller cover to apply an even coat onto the surface.

• TRUSTED QUALITY SINCE 1921 •  
**RUST-OLEUM**  
**HOME®**

# RUST-OLEUM HOME® FLOOR COATING KITS

## PRODUCT APPLICATION (cont.)

### APPLICATION (cont.)

**STEP 1:** Apply Floor Base Coat in 4'x4' sections, and maintain a wet edge while rolling. Do not let product puddle. Only one coat is recommended, wait 6 hours before applying any necessary touch-ups. **NOTE: White requires two coats,** wait 6 hours between coats. Let touched-up areas dry for 1-2 hours (dry to touch) and then Top Coat can be applied.

**OPTIONAL:** Once base coat is completely dry, additional Rust-Oleum HOME® coatings can be applied to create a designer look. Be sure to follow coating instructions and ensure the surface has thoroughly dried and is dust-free before applying top coat (Step 2).

**STEP 2:** Apply Rust-Oleum HOME® Top Coat in 4'x4' sections, and maintain a wet edge while rolling. Avoid applying too thick and do not let product puddle. Only one coat is recommended. If a second coat is desired for additional durability or uniformity, wait until the first coat is dry to touch (1-2 hours) before applying, but must apply within 24 hours. For vertical application, apply Top Coat in two thin coats. Top Coat must be abraded if recoating after 24 hours. After full system cure of 7 days, if additional coats of Base Coat and Top Coat are desired, simply clean the coated floor, reapply the Base Coat and then reapply the Top Coat.

**NOTE:** When using Rust-Oleum HOME® Anti-Slip Textured Top Coat, stir thoroughly so the texture additive is uniformly incorporated prior to use. Apply in 4'x4' sections and maintain a wet edge while rolling. Roll back between sections to blend sections together. Do not let product puddle.

**IMPORTANT:** Rust-Oleum HOME® Base Coat and Top Coat are required for the project.

## PRODUCT APPLICATION (cont.)

### DRY & TOPCOAT TIMES

For full system, allow 24 hours for light foot traffic. Allow 72 hours before replacing furniture (avoid dragging). Full cure is 7 days. Do not wash before 7 days.

### CLEAN UP AND STORAGE

Use water and mild detergent. Dried product can be removed with lacquer/thinner. Protect unused product from freezing. Fully cured floor may be cleaned with mild soap and water after 7 days. Do not use an abrasive cleaner.

### LIMITATIONS

Do not use on exterior spaces or garage floors. Do not use on interior surfaces that are sealed with a superhydrophobic sealer. Not for use inside showers. Not food safe.

### MAINTENANCE

Fully cured floor may be cleaned with mild soap and water or a general purpose cleaner such as Original Krud Kutter Cleaner Degreaser after 7 days. Do not use an abrasive cleaner.

**NOTE:** Do not leave cleaning solutions on coated surface for an extended period of time.

|  |  |                |
|--|--|----------------|
|  | <b>TECHNICAL DATA</b>                                | <b>ROC-173</b> |
| <small>• TRUSTED QUALITY SINCE 1921 •</small><br><b>RUST-OLEUM</b><br><b>HOME®</b> | <b>RUST-OLEUM HOME®</b><br><b>FLOOR COATING KITS</b> |                |

**PHYSICAL PROPERTIES**

|  |                       | STEP 1 BASE COAT   | STEP 2 TOP COAT              | CLEANER  |
|--|-----------------------|--|------------------------------|--|
| <b>Resin Type/Composition</b>                            |                       | Water-based Styrene Acrylic  | Water-based Urethane Acrylic | Proprietary Blend of Biodegradable Surfactants, Detergents and Emulsifiers |
| <b>pH</b>  |                       | NA   | NA                           | <12.2  |
| <b>Pigment</b>   |                       | Varies with color  | Aluminum Oxide, Silica       | NA   |
| <b>Solvent</b>   |                       | Water, Propylene Glycol  | Water, Glycol Ethers         | NA   |
| <b>Weight</b>  | <b>Per Gallon</b>     | 10.1-10.6 lbs.   | 8.63-8.69 lbs.               | NA   |
|  | <b>Per Liter</b>      | 1.2-1.3 kg   | 1.03-1.04 kg                 | NA   |
| <b>Solids</b>  | <b>By Weight</b>      | 47.2-51.2%   | 29.2-30.1%                   | NA   |
|  | <b>By Volume</b>      | 36.0-37.3%   | 27.3-28.1%                   | NA   |
| <b>Volatile Organic Compounds</b>                        |                       | <50 g/l  | <50 g/l                      | 0%   |
| <b>Recommended Dry Film Thickness (DFT) Per Coat</b>     |                       | 1.5-2.0 mils   | 1.0-1.5 mils                 | NA   |
| <b>Wet Film Thickness (WFT) to Achieve DFT</b>           |                       | 4.0-5.0 mils   | 4.0-4.5 mils                 | NA   |
| <b>Practical Coverage at Recommended DFT</b>             |                       | 75-100 sq. ft./kit<br>Coverage will vary depending on surface porosity and texture |                              |  |
| <b>Dry Times @ 77°F (25°C) and 50% Relative Humidity</b> | <b>Touch</b>          | 30-60 minutes  | 1 hour                       | NA   |
|  | <b>Recoat/Topcoat</b> | 6 hours  | 2 hours                      | NA   |
|  | <b>Foot Traffic</b>   | 6 hours  | 24 hours                     | NA   |
|  | <b>Normal Use</b>     | NA   | 72 hours                     | NA   |
|  | <b>Full Cure</b>      | 7 days   |                              | NA   |
| <b>Flash Point</b>                                       |                       | >200°F (93°C)  |                              | Non-Flammable  |
| <b>Shelf Life</b>  |                       | 2 years  |                              | NA   |
| <b>Safety Information</b>                                |                       | For additional information, see SDS  |                              |  |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061

Phone: 866-765-4474  
[www.rustoleum.com/rohome](http://www.rustoleum.com/rohome)

Form: ARJ-1992  
Rev.: 070623