



RUST-OLEUM® AUTOMOTIVE PEEL COAT®

DESCRIPTION AND USES

Rust-Oleum® Peel Coat® is a temporary, peelable coating designed for customizing various vehicle parts such as wheels, rims, hoods and more. It provides a high build, smooth matte finish that is washable. It is suitable for use on metal, plastic and glass surfaces. Peel Coat is a temporary coating with a service life of 6 months.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
276800	Matte White
276802	Silver
283728	Gold
283729	Matte Gunmetal
283780	Matte Red
283781	Brilliant Blue
283783	Matte Green
283784	Matte Pink
283786	Graphite
284279	Matte Black
298102	Gloss Black
323050	Galaxy Black Violet
323686	Gloss Black Cherry

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

PRIMING

A primer is not required or recommended.

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 8-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 4 or more light coats to build desired coating thickness, followed by one medium coat to achieve a smooth final film. Allow the coating to dry slightly (about 5 minutes) between coats. More coats will result in a thicker coating which is easier to remove when desired. Allow the coating to cure for 24 hours before washing. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes and can be handled in 1 hour. The film can be peeled off once the coating has fully cured. Naphtha may assist in the removal of film in intricate areas.

CLEAN-UP

When finished spraying, clear the spray valve by turning can upside down and pushing the button for 5 seconds. Allow wet paint to dry and once dry, peel away or clean up wet paint with xylene or naphtha. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as xylene or naphtha. Do not insert any object into can valve opening.

REMOVAL

When desired, Peel Coat can be easily peeled off from the surface to remove. No need to use a scraper or other such tool that could mar the surface. Simply use the pads of your fingertips, roll back the coating working from the edge, inwards toward the center of the coated object. Once the edge is lifted, grab the coating and begin to slowly peel back the coating working towards the center of the object. For best results, maintain a slow, even pull and don't over stretch the film.

It is recommended that Peel coat not remain on a surface for more than 6 months.



**RUST-OLEUM® AUTOMOTIVE
PEEL COAT®**

PHYSICAL PROPERTIES

		PEEL COAT
Resin Type	Styrene Blocked Copolymer	
Pigment Type	Varies with color	
Solvents	Blend of Acetates, Methyl Ethyl Ketone, Naphtha	
MIR	1.60 max	
Fill Weight	11 oz.	
Recommended Dry Film Thickness (DFT) Per Coat	0.5-1.0 mils (12.5-25µ)	
Practical Coverage at Recommended DFT	8 sq.ft./can (0.75 m ² /can)	
Dry times at 77°F (25°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	20 minutes
Shelf Life	5 years	
Dry Heat Resistance	200°F	
Flash Point	-156°F	
Safety Information	For Additional Information, See SDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.