



**PAINTER'S TOUCH® ULTRA COVER
BRUSH-ON PRIMER**

DESCRIPTION AND USES

Rust-Oleum® Painter's Touch® Ultra Cover Primers provide a sound base for application of Painter's Touch® Ultra Cover Brush-On Paints on heavily rusted steel. Use of a primer promotes topcoat adhesion and helps prevent chipping, cracking and peeling. Use of Painter's Touch Ultra Cover Primer eliminates the need for multiple coats of enamel finish.

PRODUCTS

½ Pints	Quarts	Description
224430T	267268	White Primer
----	1980502	Flat Gray Primer

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Apply when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply aerosol primers to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The Painter's Touch Ultra Cover Primers are compatible with most coatings, but a test patch is suggested.

PRODUCT APPLICATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. Thinning is not required. In hot, dry conditions, thin up to 2 ounces water per quart to extend dry time. Avoid painting in direct sunlight or on hot surfaces. Use a good quality synthetic brush. Avoid excessive brushing as this will reduce film thickness and protection. Use light even strokes to ensure smooth and uniform flow.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 1 hour, may be recoated in 2-4 hours and is fully dry in 2-4 hours.

CLEAN-UP

Clean brush and other application tools with soap and water.



TECHNICAL DATA

ULTRA COVER BRUSH-ON PRIMER

PHYSICAL PROPERTIES

		ULTRA COVER BRUSH-ON PRIMER
Resin Type		Water-based Acrylic
Pigment Type		Varies with Color
Solvents		Water and Glycol Ethers
Weight	Per Gallon	10.2-10.7 lbs.
	Per Liter	1.22- 1.28 kg
Solids	By Weight	51.5-55.2%
	By Volume	40.4-42.2%
Volatile Organic Compounds		<160 g/l (1.33 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5μ)
Wet Film to Achieve DFT (unthinned material)		3.5-5.5 mils (87.5-137.5μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		120 sq.ft./qt. (11.1 m ² /l)
Dry Times at 70-80°F (21-27C) and 50% Relative Humidity	Touch	1 hour
	Recoat	2-4 hours
	Fully Dry	2-4 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		>200°F (93°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.