

	<div> <div>TECHNICAL DATA</div> <div>RSD-18</div> <div> <div>ROCKSOLID®</div> <div>EFFLORESCENCE REMOVER</div> </div> </div>
---	--

## DESCRIPTION AND USES

RockSolid® Efflorescence Remover is used to remove white, chalky residue (efflorescence) and mild rust stains found on concrete and masonry. Efflorescence Remover is suitable for interior and exterior use and is safe to use near grass and plants.

RockSolid Efflorescence Remover is suitable for use on bare concrete surfaces, including garage floors, basements, driveways, carports, patios, walkways and pool decks prior to staining, sealing or coating. It can be used on freshly poured concrete. Do not apply to concrete that has already been stained, sealed or coated.

## PRODUCT FEATURES

- Removes chalky, white residue
- Brightens concrete and masonry surfaces
- Safe and easy to apply

## PRODUCT

SKU	DESCRIPTION (1 Gallon)
293438	Efflorescence Remover

## PRODUCT APPLICATION

### READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

### SURFACE PREPARATION

Proper surface preparation is critical to achieve best results. Scrape and sweep away dirt and loose contaminants on the surface. Remove any oil or grease with RockSolid Heavy Duty Cleaner (sold separately). Scrub with a stiff bristle brush or broom. Rinse thoroughly with fresh water. A power washer is preferred. Repeat as necessary to completely clean and rinse. Allow to thoroughly dry.

### MIXING

Slowly add two quarts of RockSolid Efflorescence Remover to six quarts of water in a plastic watering can (2 gallons total).

## PRODUCT APPLICATION (cont.)

### APPLICATION

For best results, use a plastic watering can or garden sprayer to apply RockSolid Efflorescence Remover. DO NOT use a metal container or garden sprayer with metal sprayer with metal parts or tips.

Apply RockSolid Efflorescence Remover where efflorescence appears on the concrete surface. The product will begin to fizz when contacting efflorescence. If necessary, use a stiff bristle broom to work the product into the surface. Wait 5-10 minutes until the fizzing stops. Repeat the application of the product until no fizzing appears. The process may require several applications.

Rinse the surface thoroughly with water or power wash to remove all product residue. Use a squeegee or broom to remove excess water from the surface. A wet/dry shop vacuum can be used. The application may need to be repeated until all salts are removed from the concrete surface.

### COVERAGE

Each gallon of concentrate will cover up to 600 square feet per gallon.

### DRY TIME

Dry time is based on 70°F and 50% relative humidity. Allow to dry for 24 hours before staining, sealing or coating.

### CLEAN-UP

Wash tools and equipment with soap and warm water. Properly dispose of all soiled rags and protect unused product from freezing.

**DANGER: CAUSES BURNS TO EYES, SKIN AND IS A RESPIRATORY IRRITANT. HARMFUL IF SWALLOWED.**

**KEEP OUT OF REACH OF CHILDREN.**

	<b>TECHNICAL DATA</b>	<b>RSD-18</b>
<small>• TRUSTED QUALITY SINCE 1921 •</small> <b>RUST-OLEUM®</b>  <small>THE WORLD'S TOUGHEST COATINGS™</small>	<b>ROCKSOLID®</b> <b>EFFLORESCENCE REMOVER</b>	

## PHYSICAL PROPERTIES

		EFFLORESCENCE REMOVER
<b>Composition</b>		Phosphoric Acid
<b>Solvent</b>		Water
<b>Weight</b>	<b>Per Gallon</b>	10.0 lbs.
	<b>Per Liter</b>	1.20 kg
<b>Volatile Organic Compounds</b>		0 g/l
<b>Practical Coverage at Recommended DFT</b>		Up to 600 sq. ft./gal. of concentrate
<b>Dry Times @ 70-80° F (21-27°C) and 50% Relative Humidity</b>		Allow to dry for 24 hours before staining, sealing or coating
<b>Shelf Life</b>		3 years
<b>Flash Point</b>		>200°F (93°C)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061

Phone: 800-373-6333  
[www.rustoleum.com/rocksolid](http://www.rustoleum.com/rocksolid)

Form: GDH-911  
Rev.: 060722