



**STOPS RUST®
TOUCH UP PAINT**

DESCRIPTION AND USES

Rust-Oleum® Stops Rust® Touch Up Paint is designed for touch up repair for indoor and outdoor metal furniture and accessories. Touch Up Paint provides excellent rust resistance, chip resistance and color retention when applied directly to metal. Touch Up Paint is packaged with a convenient brush in the cap for application in hard to reach areas. Not for use on galvanized steel.

PRODUCTS

SKU	DESCRIPTION (.45 oz.)
215057	Gloss Black
215058	Gloss White
215059	Gloss Dark Hunter Green
215110	Gloss Almond

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that will exceed 200°F (93°C). Do not use on galvanized steel.

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings. Use 7769 Rusty Metal Primer or 225135 Touch Up Rusty Metal Primer for sound rusted or clean metal before application of a finish coat. 7780 White Clean Primer is best for clean metal but may be used on sound rusted metal as well.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The Stops Rust Enamels are compatible with most coatings, but a test patch is suggested.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake well before using. Apply Touch Up Paint with even strokes. For deep scratches or chips, apply several coats a few minutes apart. If necessary, recoat within 1 to 3 hours.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures and higher humidity. Dries to the touch in 2-4 hours, to handle in 5-9 hours and can be recoated after 24 hours.

CLEAN-UP

Clean up drips and excess paint with mineral spirits or xylene.

	TECHNICAL DATA	SRT-23
	STOPS RUST® TOUCH UP PAINT	

PHYSICAL PROPERTIES

		TOUCH UP PAINT
Resin Type		Oil Modified Alkyd
Pigment Type		Varies with Color
Solvents		Mineral Spirits
Weight	Per Gallon	7.4-8.7 lbs.
	Per Liter	0.9-1.04 kg
Solids	By Weight	45.3-54.2%
	By Volume	37.0-37.2%
Volatile Organic Compounds		<490 g/l (4.07 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.5 mils (37.5-62.5 μ)
Practical Coverage at Recommended DFT		Varies with depth of scratch and surface
Dry Times at 70-80°F (21°C) and 50% Relative Humidity	Touch	2-4 hours
	Handle	5-9 hours
	Recoat	After 24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		104°F (40°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.