



ZINSSER® BULLS-EYE 1-2-3® PLUS FOR ALL PROJECTS

DESCRIPTION AND USES

Zinsser® Bulls-Eye 1-2-3® Plus Aerosols are an all purpose, primer-sealer and stain blocking primer. It blocks and seals stains caused by water, nicotine, smoke, tannin, pencil, ink, grease and felt marker, and seals smoke and pet odors. Bulls-Eye 1-2-3 Plus Aerosol can be used on any interior or exterior wood, concrete, drywall, or non-galvanized metal, including hard-to-paint surfaces such as railings, shutters and outdoor furniture. Bulls-Eye 1-2-3 Plus Aerosols are suitable for sealing spackle, drywall repairs and hiding dark colors. It sticks to glossy paint, glass and ceramic tile.

PERFORMANCE CHARACTERISTICS

- Blocks all water & oil-base stains
- Smooth finish
- Seals odors
- Sticks to all surfaces without sanding

PRODUCTS

SKU	DESCRIPTION (Aerosol)
272479	Bulls-Eye 1-2-3 Plus White
293740	Bulls-Eye 1-2-3 Plus Gray

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°-90°F (10°-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. **Do not spray indoors.** Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN.** Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray with short 'dusting' strokes, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

DRY AND RECOAT TIMES

Dries to the touch in 30 minutes. Topcoat in 30 minutes. Full adhesion and hardness develops in 7 days. Lower temperatures and higher humidity will prolong dry and cure time. Allow more time at cooler temperatures.

CLEAN UP

Wipe off tip before storing. Clean up wet paint with Xylol or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other objects into the stem.



**ZINSSER® BULLS-EYE 1-2-3® PLUS
FOR ALL PROJECTS**

PHYSICAL PROPERTIES

		BULLSEYE 1-2-3 PLUS
Resin Type		Acrylic Modified Alkyd
Pigment Type		Titanium Dioxide, Calcium Carbonate, Talc
Solvents		Acetone, Aliphatic Hydrocarbons
MIR		0.70 max
Fill Weight		13 oz.
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		10-12 sq.ft./can (0.9-1.1 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Handle	30 minutes
	Full Hardness	7 days
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.