



**ZINSSER® BULLS-EYE 1-2-3®
WITH TURBO SPRAY SYSTEM™**

DESCRIPTION AND USES

Zinsser® Bulls Eye 1-2-3® Turbo is a high hiding, all purpose, primer-sealer and stain blocker. The Turbo Spray System™ will spray up to 10" wide, allowing for faster project completing making it ideal for large projects. It blocks and seals stains caused by water, nicotine, smoke, tannin, pencil, ink, grease and felt marker and seals smokes and other odors. Use on any interior or exterior wood, concrete, drywall or non-galvanized metal. Adheres to hard-to-paint surfaces such as railings, shutters, outdoor furniture and sticks to glossy paint, glass and ceramic tile. Perfect for sealing spackle, drywall repairs and hiding dark colors.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
343746	Bulls-Eye 1-2-3 White
343748	Bulls-Eye 1-2-3 Gray

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 18-14" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. **Do not use near open flame.**

NOTE: The closer the can is held to the surface, the faster you should move the can while painting to avoid drips and sags.

DRY AND RECOAT TIMES

Based on 70°F (21°C) 50% relative humidity. Allow more time at cooler temperatures. Dries in 30 minutes. Topcoat in 30 minutes with latex or oil-base paints. For best results, allow primer to cure overnight when applying strong solvent-base topcoats.

CLEAN UP

Wipe off tip before storing. Clean up wet paint with Xylol or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other objects into the stem.



**ZINSSER® BULLS-EYE 1-2-3®
WITH TURBO SPRAY SYSTEM™**

PHYSICAL PROPERTIES

		BULLSEYE 1-2-3 WITH TURBO SPRAY SYSTEM
Resin Type		Alkyd/Solvent-Based
Pigment Type		Inorganic
Solvents		Mineral Spirits, VM&P Naptha, Acetone
MIR		0.59 max
Fill Weight		26 oz.
Recommended Dry Film Thickness (DFT) per Coat		2.0 mils (50µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		20-24 sq. ft./can
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	10 minutes
	Handle	20 minutes
	Recoat	30 minutes
Shelf Life		5 years
Flash Point		141°F (-96°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.