



# ZINSSER® ODORLESS INTERIOR OIL BASE STAIN BLOCKER

## DESCRIPTION AND USES

Zinsser® Odorless is a high solids, low VOC specialty primer formulated for interior applications where oil-base performance is required but odor is a concern. This sprayable formula is ideal for residential and commercial property maintenance.

Use on all types of bare or painted interior surfaces including wood, steel ceiling decking, drywall, plaster, concrete, stucco and masonry surfaces. It provides excellent adhesion to dense, glossy surfaces such as enamel paints and varnishes, paneling, laminates, and ceramic tile without sanding or de-glossing.

### SEALING & STAIN BLOCKING

Seals porous and moderately chalky surfaces to provide a smooth finish that is easily sanded to enhance coverage and provide consistent sheen to topcoat finishes. Zinsser Odorless tolerates pH up to 12.5 which makes it ideal for sealing porous, freshly cured plaster, cement, concrete and masonry surfaces.

Zinsser Odorless effectively blocks stains from water, nicotine, smoke, fire damage, graffiti, crayon, and pencil marks with a bright white, non-yellowing, flat finish. Two coats applied to ceilings may be left unpainted as a flat ceiling paint.

MPI #45, #136, #223 Certified. Refer to the MPI website for the most current listing of MPI certified products.

## PERFORMANCE CHARACTERISTICS

- Oil base stain blocking performance without the odor
- Formula sprays through medium sized airless pumps
- Seals difficult stains from water, fire, smoke & nicotine
- Adheres to glossy surfaces without sanding or deglossing
- Bright white, non-yellowing, flat finish can be left uncoated
- High pH resistance (up to 12.5) for concrete, plaster, stucco & joint/texture compounds
- Seals a variety of common stains like crayon, graffiti, food stains, etc.
- Compatible with oil or latex topcoats

## PRODUCTS

SKU	DESCRIPTION
03954	1 Quart
03951	1 Gallon
03950	5 Gallons

## APPEARANCE

Zinsser Odorless is white but may be tinted to off white and pastel shades by adding no more than 1 oz. universal colorant per gallon.

## PRODUCT APPLICATION

### SURFACE PREPARATION

Surfaces should be clean, dry, sound and free of dust, dirt, excessive chalky material, grime, grease, oil, wax, mildew, wallpaper, adhesive or any contamination that may interfere with adhesion. If unsure of cleanliness, always wash surface with an appropriate cleaning solution or solvent (do not use TSP as a cleaner). Remove any peeling and/or unsound coatings. Sand any remaining paint film edges smooth. When priming over stained areas, first attempt to remove as much of the stain as possible by washing, sanding, scraping, etc. Allow surface to dry completely before priming. Spot prime knots and sap streaks with B-I-N® Primer-Sealer before whole surface priming with Zinsser Odorless Stain Blocker.

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### LIMITATIONS

Zinsser Odorless is not recommended for exterior applications or for use under wallcoverings, floors, decks, roof surfaces or any surface subject to immersion or prolonged contact with water. Do not box or intermix Zinsser Odorless with other oil-base or water-base products.



# ZINSSER® ODORLESS INTERIOR OIL BASE STAIN BLOCKER

## PRODUCT APPLICATION (cont.)

### APPLICATION

**Important!** Extinguish all flames and pilot lights, and turn off all stoves, heaters, electric motors and other sources of ignition during use until project is complete.

Apply only when air, material, and surface temperatures are between 40-90°F (5-32°C) and the surface temperature is at least 5°F (3°C) above the dew point. The relative humidity should not be greater than 85%. Thoroughly mix with a drill motor to ensure any settled pigment is re-dispersed before using. DO NOT THIN.

In most cases only one coat is necessary to prime most surfaces. If excessive absorption occurs over very porous substrates a second coat may be necessary. For best results, prime entire surface before painting. Apply with a natural or synthetic bristle brush, roller, or airless sprayer. Follow manufacturer's instructions when using spray equipment.

Airless spraying - use a .017" tip at 2500 to 3000 P.S.I. Wear NIOSH approved respirator and provide adequate ventilation. Note: Compatible with water and alkyd-base topcoats. Topcoats containing lacquer thinner, MEK or similar strong solvents may soften primer and reduce gloss.

## PRODUCT APPLICATION (cont.)

### DRY TIME

Dry time is based on 70°F and 50% relative humidity. Dries to the touch in 30 minutes, can be recoated in 2 hours, and is fully cured in 7 days.

### CLEAN-UP

Clean up spills and paint drips with mineral spirits or paint thinner. Wipe up splatters before they dry. Follow equipment manufacturer's directions to clean spray equipment. Dispose of unused or unwanted product in accordance with local laws regulating solvent-based coating



**ZINSSER® ODORLESS INTERIOR OIL BASE STAIN BLOCKER**

**PHYSICAL PROPERTIES**

		<b>ODORLESS INTERIOR OIL-BASE STAIN BLOCKER</b>
<b>Resin Type</b>		Synthetic Oil-based Alkyd
<b>Pigment Type</b>		Titanium Dioxide
<b>Solvents</b>		Aliphatic and Aromatic Hydrocarbons
<b>Weight</b>	<b>Per Gallon</b>	13.1 lbs.
	<b>Per Liter</b>	1.57 kg
<b>Solids</b>	<b>By Weight</b>	77.3%
	<b>By Volume</b>	52.3%
<b>Volatile Organic Compounds</b>		350 g/l (2.9 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		1.5-2.0 mils (37.5-50µ)
<b>Wet Film to Achieve DFT (Unthinned material)</b>		3.0-4.0 mils (75-100µ)
<b>Practical Coverage at Recommended DFT (assume 15% material loss)</b>		350-400 sq. ft./gal. (8.6-9.8 m <sup>2</sup> /l) May vary with application method and surface porosity
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	30 minutes
	<b>Recoat</b>	2 hours
	<b>Stain Sealing</b>	2 hours
	<b>Full Cure</b>	7 days
<b>Shelf Life</b>		5 years
<b>Flame Spread (ASTM-84-97A)</b>		5, Class 1
<b>Smoke Contribution (ASTM-84-97A)</b>		0, Class 1
<b>Flash Point</b>		106°F (41°C)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.