



**PEEL STOP®
TRIPLE THICK SPRAY**

DESCRIPTION AND USES

Zinsser® Peel Stop® Triple Thick High Build Primer is a high performance rubberized primer that stops peeling paint by gluing down worn paint edges from previous paint jobs that can lead to topcoat cracking. Peel Stop Triple Thick is 3 times thicker than regular primers so it fills and seals cracked, weathered, and peeling areas, creating a smoother, more uniform surface for finishing. It goes on white, providing excellent hide. Use Peel Stop Triple Thick on wood, stucco, masonry, metal and vinyl siding.

PRODUCT

SKU	DESCRIPTION
278491	12 Ounce Spray

PRODUCT APPLICATION

SURFACE PREPARATION

Surfaces should be clean, dry, sound, and free of dust, dirt, grime, grease, oil, wax, mildew, or any contamination that may interfere with adhesion. Remove loose paint, dirt, and rust. For general oil and water base stain-blocking, use a Zinsser stain-blocking spray primer such as Zinsser Bulls-Eye 1-2-3 spray or Zinsser Cover Stain spray. Spot prime knots and severe stains with Zinsser B-I-N Shellac-Base Primer-Sealer spray.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Use in a well ventilated area. Apply when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Turn can upside down and continue shaking for one minute and shake occasionally during use. Hold can upright 12-18" from surface and spray with short sweeping strokes, slightly overlapping each stroke. Keep the can in motion while spraying. Keep the can the same distance from the surface. Apply multiple coats, as necessary, at no more than 10 mils wet per coat. Peel Stop can be applied up to 30 mils wet. Wait 2-3 minutes between coats. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes. Apply a latex or alkyd topcoat after 2 hours. Wait 4 hours before topcoating with two part epoxies. Peel Stop can be sanded after 4 hours.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



**PEEL STOP[®]
TRIPLE THICK SPRAY**

PHYSICAL PROPERTIES

		PEEL STOP TRIPLE THICK SPRAY
Resin Type		Kraton Rubber
Pigment Type		Titanium Dioxide and Extenders
Solvents		N-Butyl Acetate, VM&P Naphtha, Xylene
MIR		1.60 Max
Fill Weight		12 ounces
Practical Coverage at Recommended DFT (assumes 15% material loss)		Varies depending on porosity and type of surface
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Handle	1 hour
	Topcoat	After 2 hours
Shelf Life		2 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.