



PAINTER'S TOUCH® GENERAL PURPOSE SEMI-GLOSS SPRAYS

DESCRIPTION AND USES

Rust-Oleum® Painter's Touch® General Purpose Semi-Gloss Enamel Sprays are designed to provide long lasting protection and durability. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Painter's Touch General Purpose Semi-Gloss Enamel Sprays feature an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad to reduce fatigue caused by continuous spraying.

PRODUCTS

SKU (11 ounces)	DESCRIPTION
318514	Black
318517	White

COMPANION PRIMERS

SKU	DESCRIPTION
318622	White Primer
318623	Gray Primer

PRODUCT APPLICATION

PRIMING

Use of a Painter's Touch® General Purpose Primer will optimize adhesion and hiding and is recommended for bare wood and metal.

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® Original Cleaner Degreaser, commercial detergent or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

PRODUCT APPLICATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. Do not use near open flame.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat or clear coat within 1 hour or after 48 hours. Apply the clear coat in 2-3 light coats a few minutes apart.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not stick pin or other objects into the stem.

	TECHNICAL DATA	PTGP-03
	PAINTER'S TOUCH® GENERAL PURPOSE SEMI-GLOSS SPRAYS	

PHYSICAL PROPERTIES		
Painter's Touch General Purpose Semi-Gloss Sprays		
Resin Type	Acrylic Modified Alkyd	
Pigment Type	Varies by Color	
Solvents	Acetone, Methoxy, Propyl Acetate, N-Butyl Acetate, Xylene	
MIR	0.95 Max	
Fill Weight	11 Oz.	
Recommended Dry Film Thickness (DFT) per Coat	1.0-2.0 Mils	
Practical Coverage at Recommended DFT (assumes 15% material loss)	4-6 Sq. Ft.	
Dry Times at 50% relative Humidity	Touch	20 Minutes
	Handle	2 Hours
	Recoat	Before 1 Hour or After 48 Hours
Dry Heat Resistance	200°F	
Shelf Life	5 Years	
Flash Point	-4°F	
Safety Information	For additional information, see SDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.