

RUST-OLEUM®

V2100 SYSTEM HAMMERED AEROSOL

DESCRIPTION AND USES

Rust-Oleum® High Performance Hammered aerosols produce a hammered texture finish. Ideal for hiding surface imperfections, small dents and scratches. Can be applied directly to metal or over a primer to optimize corrosion protection. Not for use on galvanized steel.

This product complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

PRODUCTS

209562	Metal Silver
209563	Metal Gold
209564	Metal Dark Bronze
209590	Metal Black

PACKAGING

Aerosol containers, 15 oz net weight

COMPANION PRODUCTS

209566	White Clean Metal Primer
V2169838	Red Primer
V2182838	Gray Primer

PRODUCT APPLICATION

SURFACE PRERARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Pure Strength Cleaner/Degreaser item #3599402 or other suitable cleaner. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to dry.

STEEL: Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove loose rust, mill scale, and deteriorated previous coatings.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead.

APPLICATION

Use when temperature is above 50°F (10°C) and humidity is below 85% to ensure proper drying. Surface temperature must be between 50-100°F (10-38°C). Use primer on bare or rusted surfaces. Protect surrounding surfaces from overspray. Overspray can carry a significant distance. Shake can for one minute after mixing ball is heard. Hold can 10-14 inches from surface. Apply several light coats a few minutes apart to avoid drips and runs. Recoat within 1 hour or after 24 hours; allow more time in cooler temperatures. Two coats may be needed on rusted metal. Clean valve by turning can upside down and spray for 5 seconds. Some paint will spray out. If clogged, remove tip and clean in thinner. Do not insert any object into can valve opening.



V2100 SYSTEM HAMMERED AERSOL

PHYSICAL PROPERTIES

		HAMMERED AEROSOLS
Resin Type		Modified Alkyd
Pigment Type		Varies
Solvents		Acetone, Toluene, Xylene
Volatile Organic Compounds		<65% by weight
MIR		Max value of 1.4
Fill Weight		15 oz.
Recommended Dry Film Thickness (DFT) Per Coat		1-2 mils (25-50µ)
Practical Coverage at Recommended DFT		Approximately 14 sq. ft. (1.3 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% rel. hum.	Tack-free	10-20 minutes
	Handle	1-2 hours
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Warning!		THIS PRODUCT CONTAINS A CHEMICAL KNOWN TO THE STATE OF CALIFORNIA TO CAUSE CANCER AND BIRTH DEFECTS OR OTHER REPRODUCTIVE HARM. DANGER! EXTREMELY FLAMMABLE. MAY CAUSE FLASH FIRE. CONTENTS UNDER PRESSURE. VAPOR HARMFUL. FOR INDUSTRIAL OR COMMERCIAL USE ONLY. SEE THE PRODUCT MATERIAL SAFETY DATA SHEET (MSDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION.
Safety Information		

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.