



CAMOUFLAGE

DESCRIPTION AND USES

Rust-Oleum® Camouflage is designed to provide a non-reflective finish for hunting and sporting equipment. Various colors can be combined in a variety of patterns to blend with any terrain. Camouflage is suitable for use on vehicles, tree stands, decoys, blinds, boats and equipment. To mimic real life patterns, apply to leaves and twigs as stencils. Apply a base coat of color. Place the leaves and twigs randomly over the object to be painted. Spray over the items using three or four colors. Camouflage enamel features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

Note: Items painted with Camouflage should not be immersed in water for extended periods of time.

PRODUCTS

SKU (12 ounce spray)	Description
248661	Khaki
248662	Black
248663	Brown
248664	Olive

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Rust-Oleum primer provides added corrosion protection, enhances adhesion and hiding, and is especially recommended for metal and wood surfaces. Recommended primers include 7769830 Rusty Metal Primer and 7780830 Clean Metal Primer.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 2 or more light coats a few minutes apart. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, to handle in 1 hour and is fully dry in 24 hours. Apply a second coat or topcoat within 1 hour or after 24 hours.

CLEAN-UP

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**TECHNICAL DATA****CAMOUFLAGE****PHYSICAL PROPERTIES**

		CAMOUFLAGE
Resin Type		Modified Alkyd
Pigment Type		Titanium Dioxide and Inorganic Pigments
Solvents		Acetone and Aromatic Hydrocarbons
MIR		0.80 Max
Fill Weight		12 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50 μ)
Practical Coverage at Recommended DFT		10-12 sq.ft./can (0.90-1.09 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	20 minutes
	Recoat	Within 1 hour or after 24 hours
	Fully Dry	24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.