



UNIVERSAL BONDING PRIMER

DESCRIPTION AND USES

Rust-Oleum® Universal Bonding Primer is a fast dry, maximum adhesion white primer that firmly bonds any topcoat to difficult-to-paint surfaces, including two part epoxies. It may be used on interior or exterior surfaces to include galvanized steel, wrought iron railings, furniture, aluminum flashings, PVC, porcelain, masonry, glazed brick, metal, wood, fiberglass and other surfaces.

Universal Bonding Primer features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

SKU (12 ounce spray)	Description
286793	White Bonding Primer

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method to remove dirt. Rinse with fresh water and let dry. Remove all oil, grease, wax and petroleum based materials with mineral spirits. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 2 or more light coats a few minutes apart. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes and dries to handle in 1 hour. Apply a second coat or topcoat at anytime. For two part epoxies, wait two hours before topcoating.

CLEAN-UP

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**TECHNICAL DATA****UNIVERSAL BONDING PRIMER****PHYSICAL PROPERTIES**

		UNIVERSAL BONDING PRIMER
Resin Type		Acrylic
Pigment Type		Titanium Dioxide, Limestone
Solvents		Acetone, Methyl Ethyl Ketone, Methyl Isobutyl Ketone
MIR		0.95 Max
Fill Weight		12 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.5 mils (37.5-62.5 μ)
Practical Coverage at Recommended DFT		10-12 sq.ft./can (0.90-1.09 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Handle	1 hours
	Recoat	Apply a second coat or topcoat anytime
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877•385•8155
www.rustoleum.com

Form: GDH-621
Rev.: 052617