



RUST-OLEUM® RUST DISSOLVER JELLY

DESCRIPTION AND USES

Rust-Oleum® Rust Dissolver Jelly Removes rust from iron, steel and other ferrous metal surfaces. Also removes bluing from steel. Provides excellent clinging properties that help make the process fast and easy. Great for heavily rusted surfaces.

FEATURES

- Excellent cling
- Removes rust from metal surfaces
- Ideal for heavy rust

PRODUCT

SKU	DESCRIPTION
322435	8 Oz. Bottle

NOTE: Always test on an inconspicuous area first.

PRODUCT APPLICATION

Apply in a well-ventilated area. Apply when temperature is between 50°F and 90°F. Gloves and safety glasses are recommended for application. Not recommended for chrome or soft metals including aluminum. If applied to a painted surface, remove immediately as it will remove the paint. Do not allow product to dry on surface. Rust Dissolver Jelly is not a rust inhibitor. To provide long-term protection, apply a clear coating or prime and paint within 48 hours.

APPLICATION

Remove loose rust and dirt from surface. For heavily rusted surfaces, loosen rust with a wire brush. Liberally brush Rust Dissolver Jelly onto the surface. Wait 15-20 minutes. Rinse with clean water and allow surface to dry. Repeat process if needed. For heavy rust, a longer wait time may be required. To avoid flash rusting, dry surface with a clean cloth or place in dry atmosphere. Paint or coat the surface within 48 hours.

PHYSICAL PROPERTIES

		RUST DISSOLVER JELLY
Composition		Proprietary Blend
Weight	Per Gallon	10 lbs
	Per Liter	1.2 kg.
VOC		153
Flash Point		212°F (100°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.