

• TRUSTED QUALITY SINCE 1921 •



TECHNICAL DATA

ROC-145

METALLIC GARAGE FLOOR PAINT + PRIMER

DESCRIPTION AND USES

Rust-Oleum® Metallic Garage Floor Paint + Primer is a ready-to-use interior/exterior concrete floor paint, formulated for use on garages, carports, driveways, basements, porches, patios, walkways and pool decks. Two coats of this self-priming concrete floor paint resists damage from hot tires, motor oil, grease and gasoline. The durable, UV & weather resistant finish is easy to maintain and resists fading and peeling, and can be easily cleaned up with soap and water.

NOTE: Not recommended for use on asphalt or wood surfaces.

FEATURES

- Water-based acrylic
- Hot tire and chemical resistant
- For use on garages, driveways, patios and basements

PRODUCT

SKU	DESCRIPTION (1 Gallon)
-----	------------------------

349353	Gunmetal Metallic
--------	-------------------

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Whether over bare or previously coated concrete, proper surface preparation is critical to performance. Allow new concrete to cure for a minimum of 28 days. Before coating, if necessary, use a wire brush or sander to remove any loose or unsound concrete or masonry. Remove grease, oil, salt and other contaminants with Rust-Oleum Heavy-Duty Degreaser or Rust-Oleum Cleaner & Degreaser (sold separately). Scrub spots thoroughly with a stiff bristle brush or broom and wipe up excess cleaner with rags or paper towels to keep contaminates from spreading. Rinse thoroughly with fresh water. Repeat as necessary until completely clean.

Bare Concrete Surfaces: For proper penetration and maximum adhesion, use Rust-Oleum Concrete Etch or Rust-Oleum Clean & Etch (sold separately). Follow label instructions carefully and allow the floor to dry completely. Wipe your fingers over the clean, dry surface. If you see any dust or powder on your fingers, repeat scrubbing and rinsing until the floor is clean.

Previously Painted, Stained or Sealed Concrete

Surfaces: Use a wire brush to remove any loose or peeling paint, stain or sealer. To ensure proper adhesion, scuff sand the entire surface and clean with a solvent such as acetone.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Rust-Oleum Metallic Garage Floor Paint + Primer is ready to use. Do not thin. Apply only when air (ambient) temperature is between 50-90°F (10-32°C) and the relative humidity is below 85%. Do not paint outdoors if rain is expected within 48 hours. If using more than one gallon, intermix (box) all cans of the same product to ensure color uniformity. Stir thoroughly before applying.

NOTE: Painted floors may be slippery when wet. If desired, mix in Rust-Oleum Anti-Skid Additive (sold separately). Use a brush or edger to trim the perimeter and hard-to-reach areas. Use a long handled extension pole and a high quality $\frac{3}{8}$ " nap roller cover to apply an even coat of Rust-Oleum Metallic Garage Floor Paint + Primer onto the surface. Apply in 4'x4' foot sections and maintain a wet edge to prevent lap marks and gloss differences. Continue applying in 4'x4' sections until complete. Two coats are required. For best appearance, finish rolling in one direction. Occasional touch-up may be necessary for areas subject to heavy vehicle traffic.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Dry times increase at cooler temperatures. The surface should be ready for light foot traffic in 4-6 hours and normal foot traffic in 24 hours. FOR FULL CURE AND VEHICLE TRAFFIC, ALLOW 5 DAYS. Dry times increase at cooler temperatures.

CLEAN-UP

Wash tools and equipment with warm water and a mild detergent immediately after use. Properly dispose of all soiled rags and protect unused product from freezing.

•TRUSTED QUALITY SINCE 1921•



TECHNICAL DATA

ROC-145

METALLIC GARAGE FLOOR PAINT + PRIMER

PHYSICAL PROPERTIES

		METALLIC GARAGE FLOOR PAINT + PRIMER
Resin Type		Acrylic
Pigment Type		Carbon Black, Mica
Solvents		Water, Glycol Ether
Weight	Per Gallon	8.8 lbs.
	Per Liter	1.1 kg
Solids	By Weight	35%
	By Volume	31%
Volatile Organic Compounds		<50 g/l
Recommended Dry Film Thickness (DFT) Per Coat		1-2 mils (25-50μ)
Wet Film to Achieve DFT (unthinned material)		3-6 mils (75-150μ)
Practical Coverage at Recommended DFT (per coat)		125-250 sq.ft./gal Coverage rate can vary depending on the texture and porosity of the concrete
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Recoat	4-6 hours
	Foot Traffic	4-6 hours
	Full Traffic	5 days
Shelf Life		3 years
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 888-683-5667
www.rustoleum.com

Form: ARJ-1739
Rev.: 011019