

• TRUSTED QUALITY SINCE 1921 •



**CLEAR DRY ERASE**

**DESCRIPTION AND USES**

Rust-Oleum® Clear Dry Erase is a smooth, hard finish that creates a unique writeable-erasable surface. Apply over any color to create your own custom dry erase board. Once dry, simply use any dry erase markers to draw or write messages and then erase. Clear Dry Erase is suitable for use on interior surfaces such as drywall, wood and metal.

**PRODUCTS**

SKU	Description
284637	Clear Dry Erase

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

Surfaces must be clean, dry, and free of dirt, grease and oil. Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with detergent and water or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry. Lightly sand the surface that is to be painted. Remove dust from sanding with a lint-free cloth.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (cont.)**

**PRIMING**

Use of a clear primer provides added adhesion and hiding and is especially recommended for bare wood and other porous surfaces. Follow manufacturer's directions before applying Clear Dry Erase.

**MIXING**

Briefly stir each can before mixing. Pour Part A into Part B and stir thoroughly until the paint is uniform in color (about 2 minutes). No waiting time is required after mixing. **IMPORTANT! Apply activated Dry Erase Paint within 90 minutes of mixing.**

**APPLICATION**

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85% to ensure proper drying. With painter's tape, tape around the area you wish to paint before beginning. Pour paint into a paint tray. Use a dense foam roller that is designed to give a smooth finish. For smaller surfaces, use a foam brush. Results in a high gloss finish.

**DRY & RECOAT TIMES**

Dry and recoat times are based on 77°F (25°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 3-4 hours. After 1 hour, remove painter's tape that was used to mask the area. Then allow the Clear Dry Erase surface to cure for **3 days** before applying any markings. Once fully cured, Dry Erase markers may be applied to the surface and then wiped off with an eraser or lint-free cloth. If after erasing, a hint a marking remains, simply use a dry erase cleaner or any other general household cleaner to remove marks. Do not use abrasive cleaners, pads, or cloths. Let surface dry before using dry erase markers again.

**CLEAN-UP**

Clean brush and other application tools immediately with soap and water.

**TECHNICAL DATA**

**CLEAR DRY ERASE**

**PHYSICAL PROPERTIES**

		CLEAR DRY ERASE (ACTIVATED)
<b>Resin Type</b>		Polyamine Epoxy Blend
<b>Pigment Type</b>		NA
<b>Solvents</b>		Water, Glycol Ethers
<b>Weight*</b>	<b>Per Gallon</b>	8.8 lbs
	<b>Per Liter</b>	1.05 kg
<b>Solids*</b>	<b>By Weight</b>	46.8%
	<b>By Volume</b>	44.0%
<b>Volatile Organic Compounds*</b>		45 g/l (0.37 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		1.0-2.0 mils (25-50µ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		2.5-4.5 mils (62.5-112.5µ)
<b>Theoretical Coverage at 1 mil DFT (25µ)</b>		113 sq.ft./16 ounces activated
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		50 sq.ft./16 ounce kit
<b>Mixing Ratio</b>		3:1 Base to Activator by volume (12 ounces of Part B to 4 ounces of Part A)
<b>Induction Period</b>		None
<b>Pot Life</b>		Up to 90 minutes
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	3-4 hours
	<b>Recoat</b>	5-6 hours
	<b>Full Cure</b>	3 days
<b>Shelf Life</b>		2 years unopened containers
<b>Flash Point</b>		>200°F (93°C)
<b>Safety Information</b>		For additional information, see MSDS

\* Activated material

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.