



VARATHANE® PREMIUM FAST DRY WOOD STAIN

DESCRIPTION AND USES

Varathane® Premium Fast Dry Wood Stain is a high performance stain system enhanced with nano pigment particles. The nano pigments provide ultimate color quality and exceptional wood grain highlighting which allows for maximum color in one coat. Varathane Fast Dry Wood Stain seals wood pores and dries fast in one hour. Varathane Premium Fast Dry Wood Stain is recommended for all interior wood projects such as furniture, cabinets, doors and trim, floors and paneling. It is not recommended for exterior wood such as floors, decks or siding.

PRODUCTS

DESCRIPTION	QUART	1/2 PINT
Golden Oak	262003	262021
Spring Oak	262004	262023
Early American	262005	262024
Dark Walnut	262006	262025
Gunstock	262007	262026
Traditional Cherry	262008	262027
Black Cherry	262009	262028
Kona	262010	262029
Sun Bleached	262011	262030
Ipswich Pine	262012	262031
Traditional Pecan	262013	262032
Golden Mahogany	262014	262033
Light Walnut	262015	262034
Cabernet	262016	262035
Weathered Gray	269394	269398
Ebony	269395	269400
Antique White	297424	-----
Bleached Blue	297425	-----
Rustic Sage	297426	-----
Vintage Aqua	297427	-----
Worn Navy	297428	-----
Carbon Gray	304559	307416
Coral	307413	-----
Barn Red	207414	-----
Briarsmoke	303608	-----
Honey Maple	-----	313610
Aged Wheat	333660	333612
True Brown	333661	333616
Aged Barrel	357179	-----
Willow Gray	357180	-----

PRODUCT APPLICATION

SURFACE PREPARATION

Remove any existing finishes with sandpaper or paint stripper. Prepare bare wood for staining by sanding in the direction of the grain. Begin with #120 grit sandpaper and progress through #150, #180 and #220 grits. Before staining, remove all sanding dust and dirt with a vacuum and grease or glue with a clean rag dampened with mineral spirits.

PRODUCT APPLICATION

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

TESTING COLOR

Be sure to test your stain to verify the desired color. To test, apply the stain in an inconspicuous area.

STAIN APPLICATION

Apply when temperatures are between 60-90°F (16-38°C) and the relative humidity is below 85%. Allow longer dry times for damp, humid days. Use adequate ventilation at all times. Use full strength. Do not dilute. Stir or shake the container thoroughly before and occasionally during use.

Apply a test sample on a small inconspicuous area before proceeding with the entire job. Apply one coat of stain liberally with a good quality brush or clean lint free rag. Allow to penetrate for 2-3 minutes then remove excess by wiping with a rag in the direction of the grain. Removal of all excess material is essential to ensure proper dry time and proper adhesion of topcoat.

DRY TIME

Dry times are based on 70°F and 50% relative humidity. Dry times may be affected by temperature, humidity and ventilation. Allow more time at cooler temperatures. Fast Dry Stain dry to touch in approximately 1 hour and can be recoated in 1 hour. Allow 24 hours for full cure.

PROTECTING THE WOOD

To provide long term protection and durability, the project should be topcoated with Varathane Polyurethane. Polyurethane can be applied within 1 hour of applying the stain. Darker colors may require a slightly longer dry time.

CLEAN UP

Clean application tools and equipment with mineral spirits.

DISPOSAL

Warning! Rags, brushes, or other waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after use, place rags or waste in a sealed, water-filled metal container. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.



**VARATHANE® PREMIUM
FAST DRY WOOD STAIN**

PHYSICAL PROPERTIES

		PREMIUM FAST DRY WOOD STAIN
Resin Type		Urethane Modified Alkyd
Pigment Type		Inorganic
Solvents		Mineral Spirits
Weight	Per Gallon	7.0-8.9 lbs.
	Per Liter	0.84-1.08 kg
Solids	By Weight	35.0-53.0%
	By Volume	29.0-35.0%
Volatile Organic Compounds		500-550 g/l (4.2-4.6 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.0 mils (37.5-50µ)
Wet Film to Achieve DFT (unthinned material)		5.0-6.5 mils (125-162.5µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		225-275 sq.ft./quart 70 sq.ft./half-pint
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	1 hour
	Recoat	1 hour
	Full Cure	24 hours
Shelf Life		3 years
Flash Point		>100°F (38°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.