

• TRUSTED QUALITY SINCE 1921 •



ULTIMATE SPAR VARNISH - SPRAY

DESCRIPTION AND USES

Rust-Oleum® Ultimate Spar Varnish Aerosol provides maximum protection for all your outdoor wood projects. Rust-Oleum Ultimate Spar Varnish Aerosol is specially formulated to provide maximum protection against sun, water, weather, sea spray and chemicals, which can take years off the life of your outdoor wood. It features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort grip trigger eliminates finger fatigue cause by continuous spraying. It is ideal for all outdoor projects such as outdoor furniture, doors and window trim.

**Not Recommended for:** Decks or high traffic areas, siding or rough-sawn surfaces. This product is not intended for interior surfaces with the exception of window trim.

PRODUCTS

SKU (11 ounce spray)	Description
260346	Spar Varnish Gloss
260347	Spar Varnish Semi-Gloss
260348	Spar Varnish Satin

PRODUCT APPLICATION

SURFACE PREPARATION

To ensure proper adhesion, surfaces must be clean, dry, and free of old finishes, dust, dirt, oils or foreign matter.

**Unfinished Surface Preparation:** Sand using 150-220 grit sandpaper and remove all sanding dust using a vacuum or a tack cloth. If a filler or putty is used, make sure that it does not contain wax.

**Refurbishing existing coating:** Existing finished wood may be refurbished without complete removal of the previous coating. The surface must be free from wax, silicones, oils and other contaminants, thoroughly cleaned and abraded before applying Ultimate Polyurethane

**Stained or Painted Wood:** Follow manufacturer's direction for application of stain or paint. Make certain surface is thoroughly dry before applying Rust-Oleum Ultimate Spar Varnish. Refer to manufacturer's label for dry times. For best results, use Rust-Oleum Ultimate Wood Stains when a stained surface is desired.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

**WARNING!** If you scrape, sand or remove old paint, you may Release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

TESTING

Use care when applying over white or pastel paints or stains as discoloration may occur. Test Rust-Oleum Ultimate Spar Varnish in an inconspicuous area before beginning.

APPLICATION

Apply outdoors. Use adequate ventilation at all times. Do not apply in direct sunlight. Apply at temperatures between 55-90°F (13-32°C) and the relative humidity is below 85%. Shake can vigorously before and after use. Use a drop cloth or newspapers to protect surrounding areas from spray mist. Spray light mist coats, holding can 10-12 inches from surface. Move can with a smooth sweeping motion to avoid runs and sags. Several light coats give a better finish than one heavy coat. For hard to reach areas turn the can upside down to spray. Re-coat only when previous coats have dried clear and feel hard. (No longer feels tacky). If any coat has dried more than 24 hours, lightly sand before re-coating. For maximum durability, a minimum of 3 coats is recommended.

DRY TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Lower temperatures and/or higher humidity may cause slower dry times. Dries to touch in 1 hour and can be recoated in 2 hours. Allow finish to dry 24 hours before light use. Wait 3 days before subjecting surface to normal usage.

CLEAN UP

Use mineral spirits. Dispose of properly. For guidance on disposal of unused product, contact your local or state government environmental agency.

**TECHNICAL DATA**

**ULTIMATE SPAR VARNISH - SPRAY**

**PHYSICAL PROPERTIES**

		ULTIMATE SPAR VARNISH SPRAY
Resin Type		Urethane Alkyd Polymer
Pigment Type		NA
Solvents		Acetone, Mineral Spirits
MIR		0.65 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) per Coat		1.0-1.5 mils (25-37.5µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		40-50 sq.ft./gal. (1.0-1.2 m <sup>2</sup> /l)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	1 hours
	Recoat	2 hours
	Fully Dry	24 hours
Shelf Life		5 years
Flash Point		-141°F (-96°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.