



**X-I-M® LATEX X-TENDER™  
FLOW AND LEVELING ADDITIVE**

**DESCRIPTION AND USES**

XIM® Latex X-Tender™ is a safe, biodegradable additive designed to extend the open time for latex paints and primers. It improves the flow and leveling and can generally extend the open time 10-15 minutes for improved brush and roll application. Latex X-Tender helps to reduce ropy brush marks and improves flow and leveling of thick latex paints. It can also improve spray applications by improving the atomization of heavy bodied water-based paints at lower pressures.

**PRODUCTS**

**SKU DESCRIPTION**

11071	1-Gallon
11072	1-Quart

**PRODUCT APPLICATION**

**DIRECTIONS**

Thoroughly mix or shake well before using. Add between 2 to 6 ounces per gallon of paint (½-1½ ounces per quart). The use of Latex X-Tender will not change the overall cure time of the latex paint, but can extend the wet edge or application working time. Always check a small quantity for compatibility and the affect of the coating and the application properties before starting the project.

**PRODUCT APPLICATION**

**DIRECTIONS (cont.)**

Latex X-Tender does not change the final cured film properties. It helps improve the designed gloss of the coating. It leaves no residue in the final coating film. It will not cause paints to yellow or turn milky. It will not yellow or cloud semi-transparent or clear water-based stains or varnishes. When adding Latex X-Tender, there will be no reduction in flash rust control or sag control of the latex paint or primer.

**CLEAN-UP**

Clean up spills with water. Properly discard empty container.

**PHYSICAL PROPERTIES**

		LATEX X-TENDER
<b>Composition</b>		Water-based Additive, Propylene Glycol, Water
<b>Weight</b>	<b>Per Gallon</b>	8.3 lbs.
	<b>Per Liter</b>	0.99 kg
<b>Volatile Organic Compounds</b>		663 g/L
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		>200°F (>93°C)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.