

**RUST-OLEUM®**

# 5200 SYSTEM DTM ACRYLIC PRIMER

## DESCRIPTION AND USES

A fast-drying, low VOC, water-based acrylic copolymer primer for indoor or outdoor use in mild to moderate industrial environments. These rust inhibitive primers are designed for use on steel surfaces wherever a traditional oil-based enamel primer can be used, and dry to a matte finish. When topcoated with 5200 System DTM Acrylic, they offer excellent corrosion resistance, excellent resistance to weathering, and good resistance to mild chemical fumes and spills. Use two coats of primer on sound rusted or abrasive-blasted steel. Use 5269402 Red Primer, followed by 5281402 Gray Primer to help assure optimum hiding. Use 5281402 Gray Primer on galvanized steel.

## PRODUCTS

1-Gallon	5-Gallon	Description
5269402	5269300	Red Primer
5281402	5281300	Gray

## COMPANION PRODUCT

### RECOMMENDED TOPCOAT

5200 System DTM Acrylic  
(see corresponding Tech Data sheet CM-07)

### COMPATIBLE TOPCOATS

CV740 System 100 VOC DTM Alkyd Enamel

## PRODUCT APPLICATION

### SURFACE PREPARATION

**ALL SURFACES:** Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® Cleaner Degreaser or other suitable cleaner. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

**STEEL:** Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove all loose rust, mill scale, and deteriorated previous coatings. Abrasive blasting to a minimum Commercial Grade (SSPC-SP-6, NACE 3) with a 1-2 mil (25-50µ) surface profile is recommended for optimal performance. Abrasive blast cleaned steel requires two coats of primer.

## PRODUCT APPLICATION (cont.)

### APPLICATION

Mix thoroughly. Apply only when air and surface temperatures are between 50-100°F (10-38°C), the relative humidity is no greater than 85%, and surface is at least 5°F (3°C) above dew point. Abrasive blast clean steel requires two coats of primer. Dry times may be effected by extremely high or low relative humidity.

### EQUIPMENT RECOMMENDATIONS

**BRUSH:** Use good quality synthetic brush or short nap roller cover (¼-¾")

**AIR-ATOMIZED SPRAY:**

Method	Fluid Tip	Fluid Delivery	Atomization
Pressure	0.055-0.070	10-16 oz./min.	25-60 psi
Siphon	0.055-0.070	—	25-60 psi
HVLP (var.)	0.043-0.070	8-10 oz./min.	10 psi at tip

**AIRLESS SPRAY:**

Fluid Pressure	Fluid Tip	Filter Mesh
1800-3000 psi	0.013-0.017	100

### THINNING

**BRUSH/ROLLER:** Thinning is not recommended.

**AIR-ATOMIZED SPRAY:** Water—up to 1 pint per gallon.

### CLEAN UP

Use soap and water.

## PERFORMANCE CHARACTERISTICS

### PENCIL HARDNESS

METHOD: ASTM D3363

RESULT: 2B

### CONICAL FLEXIBILITY

METHOD: ASTM D-522

RESULT: >33%

### CYCLIC PROHESION

Rating 1-10, 10=best

METHOD: ASTM D5894, 2 Cycles, 672 hours

RESULT: Rating 10 per ASTM D714 for blistering

### IMPACT RESISTANCE (direct/reverse)

METHOD: ASTM D-2794

RESULT: >160

### TABER ABRASION

METHOD: ASTM D-4060 CS 17 wheels 500 gram load/1000 cycles

RESULT: 67 mg loss

For chemical and corrosion resistance see page 8-9 of the Rust-Oleum Industrial Brands Catalog Form #275585.

**TECHNICAL DATA****5200 SYSTEM DTM ACRYLIC PRIMER****PHYSICAL PROPERTIES**

<b>Resin Type</b>		Acrylic Copolymer Dispersion
<b>Pigment Type</b>		Titanium Dioxide, Red Iron Oxide, Zinc Phosphate, Calcium Carbonate
<b>Solvents</b>		Water, Methyl Carbitol, Propylene Glycol
<b>Weight</b>	<b>Per Gallon</b>	10.1 lbs.
	<b>Per Liter</b>	1.2 kg
<b>Solids</b>	<b>By Weight</b>	49-50%
	<b>By Volume</b>	38-39%
<b>Volatile Organic Compounds</b>		<250 g/. (2.08 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		2.0-3.0 mils (50-75 $\mu$ )
<b>Wet Film to Achieve DFT</b>		5.0-9.0 mils (125-225 $\mu$ )
<b>Theoretical Coverage at 1 mil DFT (25<math>\mu</math>)</b>		610-625 sq. ft./gal. (14.5-14.9 m <sup>2</sup> /l)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		250-350 sq. ft./gal. (5.9-8.3 m <sup>2</sup> /l)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Tack-free</b>	1-2 hours
	<b>Handle</b>	2-4 hours
	<b>Recoat</b>	1-3 hours
<b>Dry Heat Resistance</b>		200°F (93°C)
<b>Shelf Life</b>		5 years (protect from freezing)
<b>Safety Information</b>		For additional information, see SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061

Phone: 877-385-8155  
[www.rustoleum.com/industrial](http://www.rustoleum.com/industrial)

Form: GDH-481  
Rev.: 022018