

RUST-OLEUM®**6711 SYSTEM****CLEAR WATER-BASED POLYURETHANE****DESCRIPTION AND USES**

6711 is a clear, fast drying, oil-modified, single component waterborne polyurethane. This coating cures by air oxidation at ambient temperatures to give the performance of comparable single component solvent borne oil-modified polyurethanes, but at a substantially lower VOC. Designed for interior or exterior use of wood floors where a natural finish is desired. It is also useful as a base coat for the 6500 System 100% Solids High Traffic Epoxy Floor Coating, or as a sealer for concrete. It can also be used to enhance the gloss of anti-slip floor products.

This product complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

APPEARANCE

Gloss varnish which ambers slightly over time.

PRODUCTS

1 gallon containers

PRODUCT APPLICATION**SURFACE PREPARATION**

NEW WOOD: Sand wood surface smooth. Final sand with a fine grit sandpaper. Remove dust, dirt and residue. Wood should be completely dry and free of contaminants.

PREVIOUSLY VARNISHED OR STAINED WOOD: Allow oil-based stains up to seven days to dry before topcoating. Previously varnished wood or stained wood may need to be degreased and de-waxed. A combination of sanding followed by using Krud Kutter® Original Cleaner Degreaser or other suitable cleaner is recommended. On previously coated surfaces, application of a small test patch is recommended. Check for unusual appearance or adhesion problems before recoating.

CONCRETE AND MASONRY: May be used as a sealer or anti-dusting coating on fully cured concrete. The surface must be dry and free of concrete salts. Multiple coats may be necessary for the best appearance.

PRODUCT APPLICATION (cont.)**APPLICATION**

Apply only when air and surface temperatures are between 50-100°F (10-38°C) and surface temperature is at least 5° above the dew point. Do not shake or incorporate air when mixing. Gentle stirring with a paint stick is recommended. For best appearance, apply multiple coats. A minimum of three coats is needed on wood for the best appearance. Additional coats may be necessary for high traffic areas. On wood, sand lightly with an abrasive pad between coats. Do not use steel wool.

EQUIPMENT RECOMMENDATIONS

BRUSH: Use a good quality synthetic bristle. Synthetic pads, squeegee or a metering rod can also be used.

ROLLER: Short nap (up to ¼") for use on small areas. For large areas a foam type mop may be used.

THINNING

BRUSH/ROLLER/PAD: Thinning is not recommended.

AIR-ATOMIZED SPRAY: Thin with up to 5% with clean, fresh water. May sag on vertical surfaces.

CLEANUP

Soap and water, 190 Thinner or MEK for partially dried material.



TECHNICAL DATA

6711 SYSTEM CLEAR WATER-BASED POLYURETHANE

PHYSICAL PROPERTIES

		6711 SYTEM CLEAR WATER-BASED POLYURETHANE
Resin Type		Waterborne Oil-modified Polyurethane
Pigment Type		None
Weight	Per Gallon	8.6 lbs.
	Per Liter	1.03 kg
Solids	By Weight	30%
	By Volume	29%
Volatile Organic Compounds		<250 g/l (2.08 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		0.5-1.0 mils (12.5-25 μ)
Wet Film to Achieve DFT		2.0-3.5 mils (50-87.5 μ)
Theoretical Coverage at 1 mil DFT (25μ)		465 sq.ft./gal. (11.4 m ² /l)
Practical Coverage at Recommended DFT (assumes 15% material loss)		400-800 sq.ft./gal. (9.8-19.7 m ² /l)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Tack-free	15 minutes
	Recoat	30 minutes
	Light Foot Traffic	24 hours
	Scuff Resistance	4 days
Shelf Life		2 years
Safety Information		For additional information, see SDS

Calculated values are shown and may vary slightly from the actual manufactured material

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877-385-8155
www.rustoleum.com/industrial

Form: GDH-1145
Rev.: 052517