

**RUST-OLEUM®****AS6000 SYSTEM****ANTI-SLIP LOW PROFILE EPOXY****DESCRIPTION AND USES**

A two-component, anti-slip, low VOC, bare-foot grade water based epoxy with low profile. For interior or exterior use.

Specially formulated for wet areas on concrete. Easy to clean and chemical resistant. Use in barefoot and recreational areas such as pools, locker rooms, showers, laundries, walkways and other areas of light pedestrian or barefoot traffic where safety is a concern.

This product complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

**PRODUCTS**

SKU	Description
AS6082	Silver Gray
AS6086	Navy Gray

**APPEARANCE**

Flat, anti-slip finish

**PACKAGING**

Short-filled 1-gallon containers to allow for addition of AS60 Activator

**PRODUCT APPLICATION****SURFACE PREPARATION**

**NEW UNCOATED CONCRETE:** Remove oil, dirt and other chemical contaminants by cleaning with Krud Kutter® Original Cleaner Degreaser, detergent or other suitable cleaner. Rinse with water. Etch concrete with 108 Cleaning & Etching Solution. Rinse thoroughly and immediately, and allow to dry.

New concrete should be allowed to cure for 30 days before application of any coating. If there is any doubt about the dryness of the concrete, conduct a test by simply placing a weighted rubber mat, plastic sheet or other nonporous material on the surface for 24 hours. Check the underside of the mat and concrete for signs of moisture. The substrate will be darker if damp. If moisture is found, allow additional drying time (10-14 days) and repeat the test. If moisture persists, the concrete surface cannot be coated.

**PRODUCT APPLICATION cont.)**

Very dense, nonporous or chemically treated concrete may require abrasive blasting or sanding to assure proper coating adhesion. Determine porosity by pouring one ounce of water onto the concrete. If water soaks in, the surface is porous enough for coating. If water beads up on the concrete, the surface is not porous and treatment is warranted. The presence of laitance (fine white particles) will also require abrasive blasting, sanding or abrading to assure removal.

**PREVIOUSLY COATED CONCRETE:** Remove loose dirt, dust and paint by sweeping or vacuuming. Remove grease, oil, floor compound or wax as indicated above under **new uncoated concrete**. Very glossy or hard coatings should be lightly sanded to insure maximum adhesion. Concrete floor areas which require patching should be free of dirt, oil, grease, and other chemical contaminants as indicated above under **new uncoated concrete**. Loose cement and deteriorated previous paint should be removed by hand tool or power tool cleaning. The 5499 Concrete Patching Compound can then be trowel applied and allowed to cure 4 hours before applying a coating.

**APPLICATION**

Apply only when air and surface temperatures are between 50-100°F (10-38°C) and surface is at least 5°F above the dew point. Mix base component with mechanical mixer using a Jiffiler mixing blade (Rust-Oleum Product #6695) until any settled material is lifted off the bottom of the can and the material assumes a uniform appearance. Pour contents of AS60 activator can into the base component container. Mix thoroughly for 3-5 minutes until AS60 activator is uniformly dispersed. Hand mixing is not adequate and may result in improper or inadequate cure.

Use of a phenolic core roller (Rust-Oleum roller #6697) will expose the maximum amount of anti-slip aggregate, resulting in a highly ridged, irregular profile. If this is not achieved, the coating may become slippery when wet. Pour the product on the surface in a long stripe approximately 2 ft. long and 6 in. wide. Roll material in one direction only, pulling material toward you in slow straight strokes with a moderate amount of pressure. Do not over-roll or press down too heavily on the roller in an attempt to create a smooth appearance; this will adversely affect the creation of the appropriate ridged profile and the desired anti-slip characteristics. Material applied too thickly may not properly cure. Dry time may be adversely affected by extremely high or low temperature or high relative humidity. Protect applications from moisture for 12 to 24 hours after application. Protect from heavy or extended exposure to water, oil and chemicals for 5-7 days.



## TECHNICAL DATA

# AS6000 SYSTEM ANTI-SLIP LOW PROFILE EPOXY

### PRODUCT APPLICATION (cont.)

#### DRY TIMES

Dry times are based on 70°F (21°C) and 50% relative humidity. It will be suitable for foot traffic in 12 hours and will be fully cured in 48 hours.

#### THINNING

Do not thin this product

#### CLEAN-UP

Soap and water. Once coating begins to cure, 160 Thinner or MEK may be required.

### PRODUCT APPLICATION (cont.)

#### SURFACE MAINTENANCE

Maintain a clean surface to ensure that the anti-slip performance is maximized. For general purpose cleaning, use Krud Kutter® Original Cleaner Degreaser, detergent or other suitable cleaner. Scrub the surface with a stiff-bristled brush or broom. Rinse with clean water and allow to dry. Periodic touch up may be necessary in heavy traffic areas.

**TECHNICAL DATA****AS6000 SYSTEM ANTI-SLIP LOW PROFILE EPOXY****PHYSICAL PROPERTIES**

		AS6000 ANTI-SLIP LOW PROFILE EPOXY
<b>Resin Type</b>		Polyamine Epoxy
<b>Pigment Type</b>		Varies with color
<b>Solvents</b>		Water, Propylene Glycol Monomethyl Ether
<b>Weight*</b>	<b>Per Gallon</b>	11.7-13.0 lbs.
	<b>Per Liter</b>	1.4-1.6 kg
<b>Solids*</b>	<b>By Weight</b>	75-85%
	<b>By Volume</b>	65-75%
<b>Volatile Organic Compounds*</b>		70 g/l (0.58 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		10-15 mils (250-375µ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		16-20 mils (400-500µ)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		80-100 sq.ft./gal. (1.9-2.4 m <sup>2</sup> /l)
<b>Coefficient of Friction</b>		Dry: 0.78; Wet: 0.86
<b>Mixing Ratio</b>		3.7:1 base to activator by volume (use only AS60 Activator with AS6000 System)
<b>Induction Period</b>		None
<b>Pot Life @ 70°F (21°C) &amp; 50% Relative Humidity</b>		1 hour Immediately after mixing, pour the activated material on the floor in a long thin stripe.
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Foot Traffic</b>	12 hours
	<b>Heavy Traffic</b>	48 hours
<b>Shelf Life</b>		2 years (unopened containers)
<b>Flash Point</b>		>200°F (93°C) Seta flash
<b>Safety Information</b>		For additional information, see SDS

\* Activated material  
 Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
 11 Hawthorn Parkway  
 Vernon Hills, Illinois 60061  
 An RPM Company

Phone: 877-385-8155  
[www.rustoleum.com/industrial](http://www.rustoleum.com/industrial)

Form: GDH-1110  
 Rev.: 052517